

Monsanto

ORGANIC CHEMICALS DIVISION

Monsanto Company
800 N. Lindbergh Boulevard
St. Louis, Missouri 63166
Phone: (314) 694-1000

February 18, 1971

Subject: Capacitor Aroclor 1242 vs. MCS 1016

On August 6, 1970 we sent to you the proposed specifications for MCS 1016 along with copy of our specifications for Aroclor 1242, so that the typical properties of these fluids could be compared conveniently. The two fluids appear very similar.

You will recall that the purpose of MCS 1016 is to provide essentially the same characteristics as Aroclor 1242, except that higher chlorinated biphenyls have been removed, to help alleviate the PCB pollution problem.

Our goal remains to be in large scale production of MCS 1016 by July 1, 1971. Pursuant to changing to MCS 1016, we sent a drum of it to you for examination and capacitor life testing. Additional sample amounts can be made available, if needed.

Our laboratory has completed a capacitor life test study of these fluids, extending over a period of 3,200 hours and including exposure to voltage levels and temperatures considerably in excess of the conditions prescribed in the commercial acceptance tests for the fluorescent lamp ballast type capacitors used in our study. These capacitors were 2.0 microfarad units of the type rated at 580 volts AC, and required to withstand $1.5 \times 580 = 870$ volts at 70°C for 750 hours.

The severity of our test conditions is defined in the attached data. The results are essentially the same for both of the fluids and reflect excellent stability and capacitor life. While the number of capacitors tested was small (six Aroclor 1242 and five MCS 1016), the work was done under very carefully

controlled conditions in our Research Laboratory.

We have an extensive research program on materials for use in capacitor dielectric systems.

We would be most pleased to have you visit our laboratory to review not only MCS 1016 but also other work assigned to serve our mutual interests in capacitor dielectrics.

Our rather extensive new commercial facilities to produce MCS 1016 are being installed. As we are committed to the July 1, 1971 production date, please give us your findings and views from your testing work, at the earliest appropriate time.

Believing that you may like another copy of the specifications for MCS 1016 and Aroclor 1242, we are pleased to enclose them.

Best regards,

P. G. Benignus

P. G. Benignus
Market Manager
Dielectric Fluids

cs

Enclosures

DSW 325845

STLCOPCB4075790

Test Conditions, Tan δ , Capacitance, Failure Times

	70°	70°	70°	70°	70°	80°	90°	100°
Temp. °C	70°	70°	70°	70°	70°	80°	90°	100°
Voltage	870	900	900	930	965	1000	1000	1000
Time, hrs.	0	750	168	1274	168	168	168	168

[illegible][illegible]

a) Measured at 600V, room temp.
b) Measured at test voltage and temp.
* line fuse blew, measured time was 148 hrs.

CAPACITOR DIELECTRIC MCS 1016

(Similar to Aroclor 1242, except that some of the more highly chlorinated biphenyls have been removed.)

PROPERTY

TYPICAL

Appearance	Clear, colorless liquid
Color, APHA	10
Acidity (ASTM D974, D664)	0.001 mg KOH/g
Water (ASTM D1533-60)	40 ppm
Inorganic Chlorides (ASTM D1821)	0.02 ppm
Specific Gravity 25/15.5°C (ASTM D1810)	1.364
Viscosity 37.8°C (ASTM D88-56)	73.8 SUS
Refractive Index 26°C (ASTM D1807)	1.6219
Dielectric Strength (ASTM D877)	44KV
Pour Point, °C (ASTM D97-57)	-20°C
Hydrolyzable Chlorine Compounds, (ASTM D1820-65)	0.07 ppm
Hydrolyzable Chlorine Compounds, by Refluxing (ASTM D2441-65T)	0.17 ppm
Thermal Stability (ASTM D1936-64)	0.09 ppm
Distillation Range (ASTM D20-56)	10% - 327°C 90% - 342°C
Resistivity, 100°C 500 volts DC at 0.05 inch gap (ASTM D1169)	400,000 X 10 ⁹ ohm-cm. min.
Dielectric Constant (ASTM D924-49) 100 C; 60 Hz	4.88
Power Factor (ASTM D924-49) 100 C; 60 Hz	0.1%
Flash Point, Clev. open cup (ASTM D92-57)	350 to 365°F
Fire Point	None to Boiling

DSW 325847

STLCOPCB4075792

AROCLOR 1242 (Trichlorobiphenyl)
Specification Properties - September 27, 1962

<u>PROPERTY</u>	<u>TYPICAL</u>
Visc. at 37.8°C. (ASTM D88-56)	82 - 92 seconds Saybolt Universal
Specific Gravity at 25/15.5°C. (ASTM D1810)	1.381 - 1.392
Color, APHA	50 max.
Condition	Clear
Acidity, mg. KOH/g. (ASTM D974, D664)	0.01 max.
Pour Point, °C. (ASTM D97-57)	-14 or lower
Inorganic Chlorides (ASTM D1821)	0.05 ppm. max.
Refractive Index at 25°C. (ASTM D1807)	1.6240 - 1.6260
Distillation Range (ASTM D20-56)	
°C. corrected for stem and barometric pressure	10% 325 min. 90% 360 max.
Water content (ASTM D1533-60)	35 ppm. max
Resistivity, 100°C. 500 volts DC at 0.1 inch gap. (ASTM D1169)	500 X 10 ⁹ ohm-cm. min.
Dielectric constant, 100°C. at 1,000 cycles (ASTM D924-49)	4.7 to 4.9
Flash Point, Cleve. open cup (ASTM D92-57)*	170° to 200°C.
Fire Point*	None to boiling point
Sulfates (ASTM D117-31)*	None
Fixed Chlorine Content (Carius)*	43 ± 0.5%
Specific Heat at 25°C.*	0.29
Evaporation at 100°C. for 6 hrs.*	0.4% max.
Dielectric strength (ASTM I877-49) at 25°C. KV min.*	35
Hydrolyzable Chlorine Compounds, (ASTM D1820-61) ppm. chlorides, max.	0.5
Thermal Stability (ASTM D1936) ppm. chlorides, max.	0.4
Coefficient of Thermal Expansion* (ASTM D1903)	0.00068 cc./cc./°C.

*Not determined unless by special request.