

Royal Blue Intense White
Interior Trim Enamel
White
RB-32
First

Actual
3/31/42

Pigment							
451-S Lithopone	2400	67.200	3.95	94.80	4.40	105.	
1901 Titanium Oxide	1200	36.960	15.63	187.56	14.80	177.	
BI-290 Ultra. Shade Base	12	1.061	26.92	3.23	26.92	3.	
Vehicle							
(5138) Very Long Synth Solv.	2148	265.130	16.32	350.66	17.36	372.	
(2830) Mixing Varnish	702	94.680	10.43	73.22	11.02	77.	
(348) Mineral Spirits	1045	155.989	1.55	16.20	1.50	15.	
(4090) Drier	96	10.013	14.35	13.78	14.50	13.	
(4092) Drier	18	2.239	32.04	5.77	31.00	5.	
				745.11		771.	
				119.03		123.	

7621 631.222

XXXXXX

631.222
0.633
626. Gals.

1.190	1.
.021	.
.071	.
1.292	1.
.187	.
1.479	1.

L.C.L.
2.52
2.52
4.25
2.80
2.80

OVER 500.
UNDER 500.

OPA 0000757

N 4764