

Cross References

Trade Sales
Interior Gloss
One Coat Enamel
Reichhold Chemicals, Inc.
Beckosol P-296
Competitive Alkyd Resins
Release Letter #925 and 928

CG:- Mr. J. B. Bullitt, Lab.
Mr. J. W. Iliff, Lab.
Mr. G. R. E. Merkle, Lab.
Mr. H. R. Young, Lab.

Philadelphia Laboratory
June 19, 1946

"INDEXED"
Je 10'53

MEMORANDUM REPORT #M-50 (SUPPLEMENT)

INTERIOR GLOSS WHITE
ONE COAT ENAMEL

REFERENCE COPY
NOT FOR CIRCULATION

In the second paragraph under Details of Development in Memorandum Report #M-50, mention was made of a series of experiments conducted to determine the most efficient flocculating agent to use to correct the sagging tendencies of the One Coat enamel.

This supplement is being issued to provide the following tabulation of the various flocculating agents investigated and the results obtained.

<u>Code</u>	<u>Flocculating Agent</u>	<u>TM-311 B</u> <u>Sag Test</u>	<u>Flow</u>
P-639-P-45960	None	23 mm.	Sags
" 45961	1% Neofat on Pigment	19 "	Sl. too much flow
" 45962	1% Wecoline on Pigment	18 "	"
" 45963	2% Soya Lecithinon Pigment	14 "	= Standard
" 45964	2% Turkey Red Oil on Pigment	17 "	Sl. too much flow

Based on the above results, soya lecithin was selected for use in the final product.

PHILADELPHIA LABORATORY

H. E. Druce

H. E. DRUCE

HED:PL