MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE GT75' LOT 37072

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	17	2769	57	
	STUMP	Lumber	2754	

TOTAL NET WT. 2769 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
	1-23	222

N37303


O.T
181.+
169.+
166.+
152.+
174.+
168.+
154.+
162.+
174.+
159.+
168.+
186.+
153.+
160.+
178.+
156.+
109.+

20/210 CG 18 CODE GT-751-D PKG. ____

→ SEP·15·80 37072

EST. WGT. 2815 LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

17

12

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES		APPROVED BY
GT-751-D	(P)	AJC 05-09-77
GT-829-D	(A)	DCG 05-18-77
TYPED BY		
emw070279		

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN G — NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

VAT	210				
DATE	9-16				
TIME	7:15 PM				
RELEASED BY	287				
PRESS	15 & 16	17 & 18	9 & 10	21	
NO. OF CAKES	2 x 84	2 x 84	2 x 119	2 x 42	2 x 46

PRESS with AGITATION
WASH TO _____ OHMS
TEST AFTER _____ HOURS
LOAD on 4 cars

SAMPLES DELIVER TO

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1:30AM	1PM			
CAKES USED	46	20			
HRS TO FILL					
CAKE CONDITION					
NO. CARS LOADED		6			

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

Dry 14 hours at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 15

SAMPLES DELIVER TO

NO. CARS PULLED LUMP WGT. 8754

SAMPLED BY RELEASED BY

-GRINDING-

MILL 7 or 8 HSP 3/32" RP SCREEN 3560 RPM
MAX. TEMP. 200 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env
DELIVER TO C T L

~~DATE MIXED~~ 9/23/80

SAMPLED BY RELEASED BY

N37303.01

DUP050041506

37072
51
16

0.00 *

2.03 +
0.14 -
2.01 +
0.14 -
2.22 +
0.14 -
2.12 +
0.14 -
2.29 +
0.14 -
2.14 +
0.14 -
2.26 +
0.14 -
2.15 +
0.14 -
2.08 +
0.14 -
2.02 +
0.14 -
19.92 *

37072
51
16

0.00 *

19.92 +
2.02 +
0.14 -
1.93 +
0.14 -
1.91 +
0.14 -
1.81 +
0.14 -

0.65 +
0.14 -
27.54 *

5

DUP050041507