

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

LOT

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

TOTAL NET WT.

PKG. N-CODE

PROD. SPVR.

DATE _____

WHSE. OPER.

0

2 . 9 74

0.T

124.+
166.+
161.+
47.+
498.T

PRODUCT NAME = NAPHTHANIL RED DARK

NON-BLEEDING

PROCESSES

APPROVED BY

RT-539-D (N)

ALTERNATE

TYPED BY JMH

CE 40 CODE RT-539-D PKG

LOT MAY -0.81-31313

EST'D WGT 486 LBS

TOTAL EST'D WGT= LBS (CRT ENTRY)

MAKING NOTES

JOB NAME: 40RT539DPN

INSTRUCTIONS

= PRESSING =

RECORD

DATE

TIME

RELEASED BY

PRESS

NO.OF CAKES

PRESS WITHOUT

WASH TO 4000 OHMS

TEST AFTER 4 HOURS

LOAD ON 3 CARS

5-18-81

10:45

A-C

12

36

AGITATION

35-75 F WATER

PRESSLOAD

STARTED

CAKES USED

WATER ON

HRS. WASHED

OHMS

HRS. WASHED

OHMS

HRS. WASHED

OHMS

CAKE CONDITION

NO CARS LOADED

EXPLAIN LOSSES

1ST

2ND

3RD

4TH

5TH

5A

36

10PM

2

SAMPLES

DELIVER TO CTL

SAMPLED BY

RELEASED BY

= DRYING =

DRY 20 HOURS AT 180 F

LUMP: - OK - WET - SALTS - CONTAMINATD
DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO CARS PULLED

SAMPLED BY

RELEASED BY

NO DRUMS

LUMP WGT

2x, 066'

= GRINDING =

MILL #5 LSP 4-1/2" RP SCREEN 1750 RPM

MAX. TEMP. 150 F

SCREEN

RPM

MAX. TEMP.

F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV

DELIVER TO CTL

DATE MIXED 5-22-81

SAMPLED BY 389

RELEASED BY

1.54 +
0.14 -
1.65 +
0.14 -
1.68 +
0.14 -
0.60 +
0.14 -
4.91 *