MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-781 LOT 33895

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	102	5100		
	STUMP			

TOTAL NET WT. 5100 PKG. N–CODE [illegible]

PROD. SPVR.	DATE	WHSE. OPER.
WK	1/25/93	

S/S Bag 8

CG 03 CODE KY-781-D PKG. ____

→ JAN 19 33895

EST. WGT. 1018 ~~1128~~ LBS.

Impt. Use a magnetic separator in line when pressing this batch, suspect metal 4468 in batch. OK

Total Wgt. 4428#

PROCESSING INSTRUCTIONS: BATCH UNIT

22
240

PROCESSES	APPROVED BY
KY-781-D (N)	FWP 10-13-78
	AMJ 10-13-78
TYPED BY	
emw101378	

MAKING NOTES

REMARKS

NAME: KROLOR® YELLOW LIGHT

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT			223	
DATE			1-20-80	MW
TIME			10:00p	
RELEASED BY			K.A.	
PRESS	2	22	23	24
NO. OF CAKES	46	46	46	52

PRESS with AGITATION

WASH TO 5000 OHMS with 35-75°F water

TEST AFTER 4 HOURS

LOAD on 6 cars

SAMPLES 1-8 oz jar

DELIVER TO CTL for color

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9AM				
CAKES USED	52				
WATER ON	[illegible]				
HRS. WASHED	8 HRS				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	7				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

DRY 16 HOURS AT 220 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry.

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 21

SAMPLES

NO. CARS PULLED

LUMP WGT. 4750

DELIVER TO

SAMPLED BY

RELEASED BY [illegible]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050094204

33895
41
252

0.00	*
2.48	+
0.14	-
2.46	+
0.14	-
2.80	+
0.14	-
2.54	+
0.14	-
2.59	+
0.14	-
2.42	+
0.14	-
2.38	+
0.14	-
2.62	+
0.14	-
2.59	+
0.14	-
2.43	+
0.14	-
2.54	+
0.14	-
2.47	+
0.14	-
2.39	+
0.14	-
2.45	+
0.14	-
2.64	+
0.14	-
2.51	+
0.14	-
2.61	+
0.14	-
2.47	+
0.14	-
2.35	+
0.14	-
2.27	+
0.14	-
0.91	+
0.14	-
47.98	*

DUP050094205