

FILE NAME: RT Vanderbilt (RTV)

DATE: 1956 July 17

DOC#: RTV136

DOCUMENT DESCRIPTION: Confidential J-M Memo RE Microexamination of Talc from Eastern Magnesia Talc, CO., Burlington VT

CONFIDENTIAL

JOHNS-MANVILLE RESEARCH CENTER

Memorandum M412-38

Date July 17, 1956

MICROSCOPIC EXAMINATION OF TALC FROM EASTERN MAGNESIA TALC CO.,
BURLINGTON, VERMONT

An examination was made of powdered talc, supplied by Eastern Magnesia Talc Company and used by Johns-Manville Corporation. This material was compared with the three following commercial talcum powders.

Johnson and Johnson Baby Powder
Cashmere Bouquet
Mennen

The results of the examination are as follows:

- A. Eastern Magnesia Talc Company -- Over 95% of the sample was talc, $Mg_3Si_4O_{10}(OH)_2$. Of this amount, less than 10% could be considered elongated or fibrous appearing, the balance consisting essentially of platy talc particles that ranged in particle size from 125 μ to <5 μ . Total impurities were estimated microscopically to be less than 5% of the sample as follows:

Chlorite, $(Mg, Fe)_5(Al, Fe)_2 Si_3O_{10}(OH)_8$	- Major Impurity
Dolomite, $Ca, Mg (CO_3)_2$	- Minor Impurity
Pyrrhotite (V), $Fe_{1-x}S$	- Trace Impurity
Tremolite, $Ca_2Mg_5Si_8O_{22}(OH)_2$	- Minor Trace Impurity

- B. Johnson and Johnson Baby Powder -- The sample consisted essentially of talc over 90% of which was platy (particles 125 μ to <5 μ) and less than 10% of which were elongated particles. The principal impurity was dolomite present in trace amounts.
- C. Cashmere Bouquet -- The sample was essentially platy particles of talc ranging in size from 100 μ to less than 5 μ . Less than 10% of the talc was elongated particles. The sample also contained traces of dolomite and magnesite, $MgCO_3$.
- D. Mennen Talc -- The sample consisted essentially of talc over 90% of which were platy particles ranging in size from 175 μ down to <5 μ . Less than 10% of the talc particles had a fibrous or elongated appearance. Trace amounts of magnesite were present.

In my opinion, with the exception of the slightly higher impurity content, the talcum powder used by Johns-Manville is similar in mineralogical composition, particle size distribution, and shape to that of the three representative and commonly used talcum powders that were submitted for comparison.

F. L. Kadey, Jr.
F. L. Kadey, Jr.
Research Mineralogist

12

cc: C. L. Sheckler - Manville Plant (3)
E. R. Williams
A. B. Cummins
H. L. King, Jr.

CRMCM-HT-TALC-000045