

Duramix One Coat Enamel
Interior Gloss
White
A-3653
Second

				Actual 3/31/42		Market. 3/31/42	
<u>Pigment</u>							
451-E	Lithopone	3180	89.04	3.95	125.61	4.40	139.92
2030-T	Titanium Oxide	540	16.69	14.87	80.30	14.80	79.92
<u>Vehicle</u>							
(2843)G	Grind & Mix. Veh.	1530	205.02	11.12	170.14	12.12	185.44
(48)	Bodied Linseed Oil	212	26.50	14.75	31.27	17.22	36.51
(2325)	Bod. Dehy. Castor Oil	78	9.91	17.73	13.83	19.05	14.86
(5091)	Bleached Linseed Oil	246	31.91	11.38	27.99	13.62	33.61
(2499)R	Resin Solution	2036	258.98	4.34	88.36	4.62	94.06
(4090)	Drier	6	.62	14.35	.86	14.50	.87
(152)	Drier	24	3.21	13.66	3.28	14.22	3.44
(141)	Xerocene	78	11.62	1.01	.79	1.50	1.17
				542.43		589.70	
		7930	653.60	84.57		91.94	
		653.60					
		XXXXXX					
		1.87%					
		641.378					
				.846		.919	
				.015		.016	
				.035		.035	
				.896		.965	
				.187		.187	
				1.083		1.156	
				G.L.		L.C.L.	
				1.67		1.76	
				1.42		1.80	
						2.90	
				OVER 500		1.67	
				UNDER 500		1.76	
						1.85	

OPA 1 0000759

N 4766