

June 16, 1939

Kem Red Lead, 46511

Pigment by weight	61%
Vehicle by weight	<u>39%</u>
	100%

Composition of Pigment	
Red Lead	91%
Magnesium Silicate	<u>9%</u>
	100%

Composition of Vehicle	
*Synthetic Varnish	100%

*Non-volatile matter	41%
----------------------	-----

A variation of 2% either way is permissible
on the above percentages

6/24/41

KEM LUSTRAL ENAMEL LIGHT GREEN
Rex 42226

Pigment by weight	15%
Vehicle by weight	<u>85%</u>
	100%

Composition of Pigment

Chrome Green C.P.	70%
Zinc Sulfide	19%
Calcium Carbonate	<u>11%</u>
	100%

Composition of Vehicle

Synthetic Varnish	100%
-------------------	------

Non-Volatile	45%
--------------	-----

Cleveland, Ohio
May 25, 1934

Rx 43046 - Ken Transport Enamel Olive Green

APPROXIMATE COMPOSITION

Contents of Can:

Pigment by weight	11%
Vehicle by weight	89%
	<u>100%</u>

Composition of Pigment:

Lamp Black	15%
Chrome Yellow	89%
Titanium C	17%
Red Oxide	1%
	<u>100%</u>

Composition of Vehicle:

Synthetic Varnish	100%
-------------------	------

A variation of 2% either way allowable on
the above percentages

Grimm

Cleveland, Ohio
March 10, 1937

Exterior Kem Enamel Med. Yellow
Rx 48012

Contents of Can
Pigment by weight 37%
Vehicle by weight 63%
100%

Composition of Pigment
C.P. Chrome Yellow 100%

Composition of Vehicle
*Synthetic Resin Varnish 100%

*NVM 56.5%

C. B. Holton B