MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky 795-D LOT 3 2 186

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2196	1		T-208	
2170	1		T-1103	
	STUMP	Lump	4411	

TOTAL NET WT. 4366 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

CF 6/1/82

N34797

22/240

CG 03 CODE KY-795-D PKG. ____

→ DEC · 10 80 38186 12/9

EST. WGT. 1 1178 LBS.

012/A

Total Wgt: 4878# 4380

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-795-D (I)	EWK 10/6/76
	Alternate	DCG 10/7/76
	TYPED BY	
	NE 3/3/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW-MEDIUM NON-BLEEDING

INSTRUCTIONS **-PRESSING-** **RECORD**

YAT	24				
DATE	12/10/80	RM			
TIME	11:00 pm				
RELEASED BY					
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS with AGITATION

WASH TO 5000 OHMS

TEST AFTER 5 HOURS with 35-75°F water

LOAD on 5 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	12 1PM				
CAKES USED	46				
WATER ON	3 PM				
HRS. WASHED	11				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	5				
NO. CARS LOADED					

EXPLAIN LOSSES Possible color Loss 3 Bleeds Catching In Box

SAMPLES 1-8 oz JAR B1k

DELIVER TO ctl for color

SAMPLED BY #46 RELEASED BY AK

-DRYING-

Dry 14 Hrs. at 220°F

LUMPS - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums : 13

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 4411

RELEASED BY AK

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105313

0.0[illegible] +

38186
41

58
0.00

3.65 +
0.12 -
3.69 +
0.12 -
3.71 +
0.12 -
3.71 +
0.12 -
3.61 +
0.12 -
3.68 +
0.12 -
3.51 +
0.12 -
3.50 +
0.12 -
3.66 +
0.12 -
3.42 +
0.12 -
3.76 +
0.12 -
3.50 +
0.12 -
2.27 +
0.12 -
44.11 *