MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky-788 LOT 34860

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	67	3350		
	STUMP			

TOTAL NET WT. 3350 PKG. N–CODE 1130

PROD. SPVR. DATE WHSE. OPER.

3/16/80

N 27537

2D
2nd

CO 03 CODE KY-788-D PKG. ____

→ MAR13 34864

EST. WGT. ~~960~~ 1860 LBS.

OK
FP

3460

Total Wgt. ~~3560~~# Req( )

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT		240			STARTED	1				
DATE		3-13-80			CAKES USED	46				
TIME		12:15 A			WATER ON	5				
RELEASED BY		337			HRS. WASHED	4				
PRESS	22	23	24		OHMS	1000				
NO. OF CAKES	46	46	46		HRS. WASHED					
PRESS With AGITATION					OHMS					
WASH TO 2000 OHMS with 35-75° F water					HRS. WASHED					
TEST AFTER 2 HOURS					OHMS					
LOAD on 6 cars					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

AK

SAMPLES 1- 8oz JAR
DELIVER TO CTL for Color

SAMPLED BY 197 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F L.T. H.V.
Then Dry 8 hrs at 160 °F T.T.

LUMPS - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums 14

SAMPLES
DELIVER TO

NO. CARS PULLED 6 LUMP WGT. 3372
SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F


EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094696

N 27537.01



DUP050094697