

1 & 122  
New Era House Paint  
White  
Analysis

|         |                |
|---------|----------------|
| Pigment | Weight         |
| Vehicle | 66.00 %        |
|         | <u>34.00 %</u> |
|         | 100.00 %       |

|                            |               |
|----------------------------|---------------|
| Pigment                    |               |
| (1) White Lead             | 31.00 %       |
| Zinc Oxide                 | 30.00 %       |
| Titanium Magnesium Pigment | 34.00 %       |
| Titanium Dioxide           | <u>5.00 %</u> |
|                            | 100.00 %      |

|             |               |
|-------------|---------------|
| Vehicle     |               |
| Linseed Oil | 92.00 %       |
| Japan Drier | <u>8.00 %</u> |
|             | 100.00 %      |

|                                |       |
|--------------------------------|-------|
| (1) Basic White Lead Carbonate | 60. % |
| Basic White Lead Sulphate      | 40. % |

3-31-42

OPA

0000777

N 4774