

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81

LOT MAY -0-81-E1429

ALTERNATE
TYPED BY JMH

EST'D WGT 5632

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YE698DPS

INSTRUCTIONS				= PRESSING =	RECORD										
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
242	5-16	7:00 P	JDL	2	92	93	54	54	54	STARTED	8:45				
										CAKES USED	32				
										WATER ON	5:00				
										HRS. WASHED	1/2				
										OHMS	2000				
										HRS. WASHED					
										OHMS					
										HRS. WASHED					
										OHMS					
										CAKE CONDITION	6				
										NO CARS LOADED					
										EXPLAIN LOSSES					

SAMPLES
DELIVER TOSAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F | LUMP: - OK - WET - SALTS - CONTAMINATED

(NOT EXTRUDED) DRY 10 HRS AT 240 F

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LABNO CARS PULLED
SAMPLED BY
RELEASED BYNO DRUMS
LUMP WGT

5537

= GRINDING =

MILL MIKROATOMIZE	SCREEN	RPM	SCREEN	RPM
MAX. TEMP	DEG F		MAX. TEMP.	F
SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW				

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1429
124
41

3.46 +
0.14 -
3.54 +
0.14 -
3.57 +
0.14 -
3.67 +
0.14 -
3.59 +
0.14 -
3.39 +
0.14 -
3.64 +
0.14 -
2.00 +
0.14 -
25.74 *

1429
124
41

3.36 +
0.14 -
3.46 +
0.14 -
3.61 +
0.14 -
3.41 +
0.14 -
3.33 +
0.14 -
3.46 +
0.14 -
3.47 +
0.14 -
3.41 +
0.14 -
3.38 +
0.14 -
25.74 +
55.37 *