MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 908 LOT 34509

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	71	3550		

STUMP

TOTAL NET WT. 3550 PKG. N–CODE 438

PROD. SPVR. DM DATE 3/4/89 WHSE. OPER.

CG 03 CODE KY-908-D PKG. _____

→ FEB23 34502

EST. WGT. 949 LBS.

Total Wgt. 3549 #

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-908-D (E)	EWK 12/12/77
Alternate	DCG 12/14/77
TYPED BY	
rj 2/14/78	

MAKING NOTES

REMARKS

NAME: Krolor® Yellow - Light NON-BLEEDING

INSTRUCTIONS		-PRESSING-				RECORD					
VAT		240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		2-23				STARTED	1P				
TIME		11PM				CAKES USED	240				
RELEASED BY						WATER ON	5Hr				
PRESS	2	22	23	24		HRS. WASHED	5½				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS with		AGITATION				HRS. WASHED					
WASH TO	2000	OHMS with 135-145°F water				OHMS					
TEST AFTER	2	HOURS				HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION	OK				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO Ctl for color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

DRY 24 HOURS AT 180 °F

Dry on first stage only.
Reset every 5 hr til dry.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3604
RELEASED BY [illegible]

-GRINDING-

3/32

MILL 939 HSP ~~1/8~~" RP SCREEN 3500 RPM
MAX. TEMP. 170 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094771

34502
4100
158

0.00 *

3.40 +
0.12 -
3.27 +
0.12 -
3.44 +
0.12 -
3.24 +
0.12 -
3.54 +
0.12 -
3.25 +
0.12 -
3.37 +
0.12 -
3.26 +
0.12 -
3.37 +
0.12 -
3.35 +
0.12 -
3.19 +
0.12 -
0.80 +
0.12 -
36.04 *

DUP050094772