31/213

CG 18 CODE GC-1-A PKG.

→ OC 16 37485

EST. WGT. 2166 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(C) GC-1-A	AJC 1-10-78
	DCG 1-13-78
TYPED BY	
NSA 3-14-78	

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN G EC

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT	213					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-22-80					STARTED	7:39				
TIME	8:45 AM					CAKES USED	44				
RELEASED BY	[illegible]					WATER ON	11A				
PRESS	31					HRS. WASHED	21				
NO. OF CAKES	44					OHMS	350				

PRESS with AGITATION

WASH TO 3000 OHMS 135-145°F water

TEST AFTER 20 HOURS

LOAD in metal drumsat 360# net wgt.

NOTE: 1. Request making reheat SV to 178-182°F once per shift

2. Air-blow presscake when 3000 ohms reached for 15 min at 40 PSI

HRS. WASHED	
OHMS	
HRS. WASHED	
OHMS	
CAKE CONDITION	
NO. CARS LOADED	

EXPLAIN LOSSES

SAMPLES Thief sample per SOP +1 QT

DELIVER TO CTL

SAMPLED BY RELEASED BY

-DRYING-

DO NOT DRY

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

NO. CARS PULLED LUMP WGT.

DELIVER TO

SAMPLED BY RELEASED BY

-GRINDING-

MILL	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

DATE MIXED

SAMPLES

DELIVER TO C T L

SAMPLED BY RELEASED BY

0.T

116.+
106.+
100.+
112.+
103.+
70.+
133.+
120.+
99.+
110.+
74.+
81.+
102.+
76.+
112.+
85.+
83.+
72.+
99.+
61.+
95.+
77.+
90.+
84.+
93.+
112.+
109.+
57.+

2631

2631.T

DUP050041565