April, 1971



PLICAST AIR LITE

Formula

Vermiculite	45%
7m Asbestos	10%
H. E. Portland Cement	45%
	100%

Ingredients

Vermiculite: 1/8"-0, local source.

Asbestos: From Chicago Firebrick Co., Chicago or local source in 50# bags.

Cement: Local source.

Mixing

Dry ingredients thoroughly mixed and packed in 50# bags.

