

evm
J. E. Southwick

June 28, 1972

Coatings & Resins Research Center
Strongsville, Ohio

Mr. S. T. Howell
cc: Mr. R. J. Haviland
Mr. H. M. Werner
Mr. M. Malaga
Mr. W. M. Tomc
Mr. J. G. Kingston

Lead Removal Formulas
Y-5634D, Y-5734C

The subject formulas are being issued to remove all lead compounds. Lead drier feeder is being replaced by cobalt drier feeder E398. Zirconium and cobalt driers are again being used to replace lead drier. For Y-5634, Silcron G100 (N320) replaces N318. This completes the conversion to Glidden silica. Y-5634 is made in Reading and Y-5734 is buy out from Wooster Finishes.

JES:jm

J. E. Southwick

N 4069

GLD012129