

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky. 908LOT 34517

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1770</u>	<u>1</u>	<u>T. 118</u>		
<u>1760</u>	<u>1</u>	<u>T. 38</u>		

STUMP

TOTAL NET WT. 3530

PKG. N-CODE _____

PROD. SPVR. SM

DATE

WHSE. OPER.

3/1/80

CG 03 CODE KY-908-D PKG. _____
→ FEB 25 34517
EST. WGT. 949 LBS.

TOTES

OK
FP

PROCESSING INSTRUCTIONS: BATCH UNIT

$\frac{23}{240}$	PROCESSES KY-908-D (D)	APPROVED BY EWK 12/12/77 DCG 12/14/77
	TYPED BY	
	pri 1/31/78	
	MAKING NOTES	
REMARKS		

TOTAL WGT. 3549#

NAME: DROLOR® YELLOW- LIGHT

NON-BLEEDING

INSTRUCTIONS				-PRESSING-	RECORD				
VAT				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				STARTED	6 PM				
TIME				CAKES USED	54				
RELEASED BY				WATER ON	10 PM				
PRESS	2	22	23	HRS. WASHED	5				
NO. OF CAKES	46	46	46	OHMS	2500				
PRESS with		AGITATION			HRS. WASHED				
WASH TO	2000	OHMS with 135-145°F water			OHMS				
TEST AFTER	2	HOURS			HRS. WASHED				
LOAD	On 6 cars				OHMS				
				CAKE CONDITION					
				NO. CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES 8 oz Jar
DELIVER TO CIL for color

SAMPLED BY #52 RELEASED BY JR

-DRYING-

DRY 24 HOURS AT 180 °F	LUMP: - OK - WET - SALTS - CONTAMINATE
Dry on first stage only. Reset every 5 hr til dry.	
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 11
SAMPLES	NO. CARS PULLED
DELIVER TO	SAMPLED BY
	RELEASED BY JR

-GRINDING-

MILL 939 HSP 1/8" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 170°F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING		DATE MIXED	
SAMPLES 1 ENV & 1 PT Can			
DELIVER TO CIL		SAMPLED BY	
		RELEASED BY	

DUP050094768

34517
4100
158

0.00 *
3.51 +
0.12 -
3.36 +
0.12 -
3.31 +
0.12 -
3.40 +
0.12 -
3.43 +
0.12 -
3.06 +
0.12 -
3.26 +
0.12 -
3.29 +
0.12 -
3.43 +
0.12 -
3.44 +
0.12 -
3.21 +
0.12 -
35.38 *