

Case: 48106-3
Ref.: 1621

Bell Laboratories

600 Mountain Avenue
Murray Hill, New Jersey 07974
Phone (201) 582-3000

January 20, 1983

Mr. Jack O'Erien
New York Telephone
Room 1650
2 Pennsylvania Plaza
New York, N. Y. 10121

Dear Jack:

Here are the results for your bulk samples of sprayed-on insulation taken January 4, 1983 from 111 Livingston Street, Brooklyn.

The two samples were analyzed for asbestos content by polarized light microscopy at Bell Laboratories.

Ground Floor
Sample


Some asbestiform, birefringent fibers with low relief were seen. Dispersion staining in a medium of 1.550 refractive index indicated the presence of the chrysotile form of asbestos. Most of the sample is crystals and glass fibers.

Basement Ceiling
Sample

Very few asbestiform birefringent fibers with low relief were seen. Dispersion staining indicated the presence of chrysotile. The remainder of the sample is crystalline.

If you have any questions, please call me at (201)-582-7519.

Sincerely,


Thomas J. Hartman

MH-78691-TJH-mib

Copy to
G. H. Collings, Jr., M. D.
P. H. Stark - NYT
J. M. Degen - AT&T
R. W. Stone, M. D.

W. J. Schreiber
G. M. Wilkening

CONFIDENTIAL

003630