

INTER-OFFICE MEMO

TENNECO CHEMICALS, INC.

TO A. Stasenko AT Burl. Compound DATE September 23, 1969

FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr

SUBJECT Union Carbide 250 Resin W. O. Champion

Conoco 225 Resin H. H. Duhamel

 P. Gawason

 P. R. Scarito

 D. H. Weintraub

 File

The results of Union Carbide 350 resin and Conoco 225 resin received on 9/22/69 are as follows:

Union Carbide

<u>Properties</u>	<u>Truck #107</u>	<u>Truck #285</u>	<u>Burl. 250-12 Spec.</u>
Relative Visc.	2.48	2.48	2.40 - 2.48
Gel	49	49	12 Maximum
Dry Blend	5.0	4.4	6.0 - 8.0
Screen			
+40	-	-	-
+60	Tr	Te	0-3
+80	9	7	-
+100	54	56	50 - 80
+140	89	89	-
+200	98	99	-
Thru	2	1	0 - 5

Conoco

<u>Properties</u>	<u>Conx - 45280</u>	<u>Conx - 44652</u>	<u>Burl. 225/16R Spec.</u>
Relative Visc.	2.23	2.31	2.26 - 2.33
Gel	21	13	13 Maximum
Dry Blend	6.7	6.6	6.0 - 8.0
Screen			
+40	-	-	-
+60	Tr	Tr	0 - Tr
+80	19	16	-
+100	58	60	40 - 70
+140	86	91	-
+200	95	98	-
Thru	5	2	0 - 5
Volume Resist.	6.8	6.9	10 Maximum

ELK/rjl

E. L. Kanyok
COLORITE 015873