

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 787 LOT 37249

NET WT/PKG NO. PKG PACK. WGT LOCATION PO

1704 1 T-841712 1 T-294STUMP Lump - 3,413TOTAL NET WT. 3416 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

JIT 10/7/80

N34926

CG 03 CODE KY-787-D PKG. _____
→ SEP-28-80 37249
EST. WGT. 1000 932 LBS.

OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

22 1240	PROCESSES KY-787-D (Q)	APPROVED BY EWK 9/22/76 DCG 9/27/76
	RETYPE BY CJH 4/2/80	
	MAKING NOTES	

REMARKS

TOTAL WGT 3332#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
VAT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-1-80				STARTED	8A				
TIME	7:30A				CAKES USED	53				
RELEASED BY	C.M.				WATER ON	1:30PM				
PRESS	22	23	24	25	HRS. WASHED	3				
NO. OF CAKES	46	46	52	48	OHMS	2800				
PRESS WITH	AGITATION				HRS. WASHED					
WASH TO	2000	OHMS WITH 35-75 F WATER			OHMS					
TEST AFTER	2	HOURS			HRS. WASHED					
LOAD ON	6 CARS				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	5	71			
					EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY _____ RELEASED BY 131

-DRYING-

DRY 12 HRS AT 220 °F THEN DRY 6 HRS AT 160 °F	LUMP: - OK - WET - SALTS - CONTAMINATED
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO. DRUMS 14
DELIVER TO	NO. CARS PULLED SAMPLED BY LUMP WGT. 3413 RELEASED BY <u>131</u>

-GRINDING-

MILL 939 HSP 3/32" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 150 °F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING	DATE MIXED		
SAMPLES 1 ENV & 1 PT. CAN			
DELIVER TO CTL	SAMPLED BY	RELEASED BY	

DUP050105846

37249

41

17

0.00 +
0.00M+

2.71 +

0.12 -

2.50 +

0.12 -

2.57 +

0.12 -

2.66 +

0.12 -

2.80 +

0.12 -

2.78 +

0.12 -

2.68 +

0.12 -

2.72 +

0.12 -

2.66 +

0.12 -

2.59 +

0.12 -

2.69 +

0.12 -

2.53 +

0.12 -

2.33 +

0.12 -

4.59 +

0.12 -

34.13 *

34.13M+