

Vista Polymers

Highway 25
P. O. Box 91

Aberdeen, MS 39730

A

To: Mark Manion

Date Fax Sent: 8/13/92

OFFGRADE RAILCAR

Railcar No.: VIPX 45795

Product: Debox

Load Date: 7/26/92

Ship Date: 8/27/92

Customer: Weyford Location: Thomasville, GA

Order No: 0015401-000

COMPARTMENT

PROPERTY	A	CA	CB	B
Moisture, %	0.15	0.11	0.14	0.07
Contamination, Blk.	10	200	20	200
Contamination, Brn.	69	2000+	100	1000+
Bulk Density, gm/cc	0.527	0.528	0.520	0.528
Particle Size Distribuion				
% on 40 Mesh	0.0	0.0	0.0	0.0
% thru 140 Mesh	18.9	8.8	17.6	10.6
% on Pan	5.7	3.3	5.7	14.1
L Color	99.70	99.77	99.96	99.92
b Color	2.12	0.86	2.05	0.77
Inherent Viscosity (Top)	0.961	0.976	0.959	0.975
Inherent Viscosity (Bot)	0.837	0.885	0.870	0.854
RVCM	0.233	1.146	0.261	1.623

Amy E. Bagwell
Laboratory Supervisor

VAB.0001204737

Vista Polymers

Highway 25

Aberdeen, MS 39730

PVC RAILCAR ANALYSIS OFFGRADE

Load Date: 7-26-92 Product: DEBOX Car No.: 45795
Time Logged In: 0200 Logged In By: D.T. Silo(s): 681+682
Ship Date: _____ Order No: _____ Customer: _____

COMPARTMENT	A		CA		CB		B	
Moisture %	.15		.11		.14		.07	
Contamination	10 / 69		200 / 2000		20 / 100		20 / 1000	
Bulk Density	527		.528		.520		.528	
Color "L"	99.70		99.77		99.76		97.72	
Color "a"	.14		.95		.06		.97	
Color "b"	2.12		.86		2.05		.77	
Static Flow	0 / 8.7		0 / 8.0		0 / 9.6		0 / 7.5	
Viscosity	Top	Bottom	Top	Bottom	Top	Bottom	Top	Bottom
	.961	.837	.976	.885	.959	.870	.975	.854
RVCM	.233		1.146		.261		1.623	

Screen Analysis

	Mesh	40	60	80	100	120	140	200	Pan
A	Weight	0.0	0.91	9.49	10.39	10.99	8.81	6.58	2.85
	%	0.0	1.8	19.0	20.8	21.9	17.6	13.2	5.7
CA	Weight	0.0	1.38	15.61	13.61	10.43	4.80	2.50	1.64
	%	0.0	2.8	31.2	27.2	20.9	9.6	5.0	3.3
CB	Weight	0.0	0.55	11.18	11.20	10.47	7.76	5.93	2.85
	%	0.0	1.1	22.4	22.4	21.0	15.5	11.9	5.7
B	Weight	0.0	1.24	14.09	13.22	11.00	5.30	3.27	2.03
	%	0.0	2.5	28.2	26.4	21.7	10.6	6.5	4.1

Technician: RJ+JS

VAB.0001204738