CODE Ry 908 LOT E1033

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1890	1	T-	298	
1670	1	T-	71	
	~~STUMP~~	Lump-	3,554	

TOTAL NET WT. 3560 PKG. N-CODE

PROD. SPVR. [illegible] DATE 5,5,81 WHSE. OPER.

PRODUCT NAME = [illegible]

CG 03 CODE KY-908-D PKG ____

LOT MAY -0·81-Σ1033

EST'D WGT 1~~0~~3 LBS

TOTAL EST'D WGT=~~6203~~ 3549 LBS (CRT ENTRY)

32
262

PROCESSES APPROVED BY
KY908D(F) FWP 01/27/81
ALTERNATE
TYPED BY WRT/JMW

MAKING NOTES

JOB NAME: 03KY908DPF

= PRESSING =

INSTRUCTIONS

VAT			262
DATE			5-1-81
TIME			8:30P
RELEASED BY			
PRESS	96	95	324
NO.OF CAKES	72	72	

PRESS WITH AGITATION
WASH TO 2000 OHMS - 135-145 F WATER
TEST AFTER 3 HOURS
LOAD ON ~~10~~ 6 CARS

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9pm				
CAKES USED	40				
WATER ON	1				
HRS. WASHED	3				
OHMS	2.000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	5				

EXPLAIN LOSSES

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

SAMPLES
DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 12
NO CARS PULLED 5 LUMP WGT 3554
SAMPLED BY
RELEASED BY

= GRINDING =

MILL 939 HSP 1/8"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050096276

1033
41
124

0.00 *

3.40 +
0.12 -
3.27 +
0.12 -
3.25 +
0.12 -
3.23 +
0.12 -
3.40 +
0.12 -
3.31 +
0.12 -
3.33 +
0.12 -
3.31 +
0.12 -
3.35 +
0.12 -
3.16 +
0.12 -
2.93 +
0.12 -
1.04 +
0.12 -
35.54 *

DUP050096277