

ORIGINAL	X-A	X-B
TENSILE	1363	1665
ELONGATION	396	341
DUROMETER	56 → 55	60 → 58
MOD @ 100%	345	510
" @ 200%	665	1025
" @ 300%	1009	1429
COMP SET $\frac{2}{100}$	59.5%	73.6%
PLIED TO SET		
AIR AGING 70 HRS 158°F		
TENSILE	1438 +5.5%	1748 +5%
ELONGATION	332 -16.2%	298 -12.6%
DUROMETER	60 → +4 58 +3	65 → +5 62 +4
WT LOSS	-23%	-1.9%
AIR AGING 70 HRS 212°F		
TENSILE	1411 +3.5%	1752 +5.2%
ELONGATION	290 -26.8%	339 -0.6%
DUROMETER	55 → -4 51	57 → -3 54
WT LOSS	-1.5%	-2.0%
SP. GRAV.	1.23	1.27

CHARDO 00832

PHYSICAL TEST SHEET

STOCK V-6004 MIXED FACT

CURED

TESTED 3-87

[illegible]

CHARDO 00833