

1 & 122
New Era House Paint
White
Analysis

Pigment	Weight
Vehicle	66.00 %
	34.00 %
	100.00 %

Pigment	Weight
(1) White Lead	31.00 %
Zinc Oxide	30.00 %
Titanium Magnesium Pigment	34.00 %
Titanium Dioxide	5.00 %
	100.00 %

Vehicle	Weight
Linseed Oil	92.00 %
Japan Drier	8.00 %
	100.00 %

(1) Basic White Lead Carbonate	60. %
Basic White Lead Sulphate	40. %

3-31-42

OPA

0000777

N 4774