

PROCESSES APPROVED BY
YE-698-D (S) F.ROST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

TOTAL EST'D WGT= LBS (CRT ENTRY)

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS
NO. OF CAKES
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

[illegible]

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

== DRYING ==

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY *gal*
RELEASED BY

NO DRUMS
LUMP WGT 5954

GRINDING

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTE

DATE MIXED
SAMPLED BY
RELEASED BY

1443
4100
18

158

0.00 *

0.00 *
3.35 +
0.14 -
3.38 +
0.14 -
3.41 +
0.14 -
3.44 +
0.14 -
2.45 +
0.14 -
15.33 *

24.13 +
3.81 +
0.12 -
3.28 +
0.12 -
3.25 +
0.12 -
3.53 +
0.12 -
2.74 +
0.12 -
40.14 *

158

0.00 *

15.33 +
3.68 +
0.12 -
2.94 +
0.12 -
2.54 +
0.12 -
24.13 *

1443
41
305

0.00 *

40.14 +
3.42 +
0.12 -
3.13 +
0.12 -
3.15 +
0.12 -
3.26 +
0.12 -
3.44 +
0.12 -
2.92 +
0.12 -
0.92 +
0.12 -
59.54 *

20