

EXHIBIT "A"

TO MINUTES OF THE

RED LEAD TECHNICAL COMMITTEE MEETING

MARCH 18, 19, 20, 1968

INSPECTION RECORD - ATMOSPHERIC EXPOSURE

4" x 4" x 3/8" Angle Specimens

Wire Brushed - Solvent Cleaned

45° - South Exposure

Project No. 1Date Exposed 5/9/43Date Inspected 3/18/46Elapsed Time 58 months

Panel No.	Paint No.	New		One Coat Primer Area Corrosion		Two Coat Primer Area Corrosion		Comments
		P.	V.	Edge	Gen.	Edge	Gen.	
LL89A	3	5	8	6	10	10	10	1st Choice of Series
LL88A	2	6	9	4	10	10	10	2nd Choice of Series
LS07A	21	5	4	5	10	10	10	3rd Choice of Series
LL88AD	2	6	9	7	10	10	10	
LL90A	4	6	8	3	10	7	10	
LL90AD	4	6	8	2	10	7	10	
LL92A	6	6	10	1	9	8	10	
LL92AD	6	6	10	2	9	8	10	
LL94A	8	6	1	1	10	4	10	
LL94AD	8	6	1	1	9	5	10	
LL96A	10	6	2	1	10	6	10	
LL96AD	10	6	2	1	9	7	10	
LL98A	12	6	3	1	10	5	10	
LL98AD	12	6	3	1	10	6	10	
LS02A	14	6	13	0	9	5	9	
LS02AD	14	6	13	0	7	5	9	
LS05A	19	6	4	4	10	9	10	
LS05AD	19	6	4	4	10	8	10	
LS08A	22	6	4	4	10	10	10	
LS08AD	22	6	4	4	10	10	10	
LL87A	1	5	9	3	10	10	10	
LL87AD	1	5	9	4	10	10	10	
LL89AD	3	5	8	6	10	10	10	
LL91A	5	5	10	4	10	10	10	
LL91AD	5	5	10	4	10	10	10	
LL93A	7	5	1	1	10	7	10	

*Vehicle #4, R.O., L.L.O.

**Vehicle #4, R.O., F.R.O.

INSPECTION RECORD - ATMOSPHERIC EXPOSURE

4" x 4" x 3/8" Angle Specimens
Wire Brushed - Solvent Cleaned
45° - South Exposure

Project No. 1
Date Exposed 5/9/43
Date Inspected 3/18/48
Elapsed Time 58 months

Panel No.	Paint No.	New		One Coat Primer Area Corrosion		Two Coat Primer Area Corrosion		Comments
		P.	V.	Edge	Cent.	Edge	Cent.	
4493AD	7	5	2	1	10	8	10	
4495A	9	5	2	5	10	9	10	
4495AD	9	5	2	7	10	10	10	
4497A	11	5	3	2	10	7	10	
4497AD	11	5	3	3	10	8	10	
4506A	20	5	4	4	10	10	10	
4506AD	20	5	4	3	10	9	10	
4507AD	21	5	4	5	10	10	10	
4512A	26	5	7	3	9	8	10	
4512AD	26	5	7	2	8	9	10	
4513A	27	5	6	5	10	9	10	
4513AD	27	5	6	5	10	9	10	
4509A	23	6	12	4	4	7	8	Top Coat Cracked
4509AD	23	6	12	5	5	8	9	
4511A	25	6	7	3	9	7	10	
4511AD	25	6	7	4	9	8	10	
4514A	28	6	6	2	10	6	10	
4514AD	28	6	6	3	10	7	10	
4509A	13	(1)	1	0	9	7	10	
4509AD	13	(1)	1	0	9	9	10	
4500A	14	(2)	1	0	9	5	10	
4500AD	14	(2)	1	0	8	6	10	
4501A	15	(3)	1	0	9	4	10	
4501AD	15	(3)	1	0	8	3	10	
4515A	29	CORL		1	10	7	10	

Vehicle #4, RLO, 2, 10.

- (1) 10% iron oxide in place of ZNO in Fig. 6
(2) 7% Dicalite in place of Ash. in Fig. 6
(3) 7% Ash., 3% Dicalite in place of iron oxide in Fig. 6

INSPECTION RECORD - ATMOSPHERIC EXPOSURE

4" x 4" x 3/8" Angle Specimens
Wire Brushed - Solvent Cleaned
45° - South Exposure

Page No. 3

Project No. 1
Date Exposed 5/9/43
Date Inspected 3/18/44
Elapsed Time 58 months

Panel No.	Paint No.	New P.	V.	One Coat Primer Area Corrosion		Two Coat Primer Area Corrosion		Comments
				Edge	Gen.	Edge	Gen.	
4515AD	29	QDR		2	10	6	10	
4503A	17	Navy 84		4	9	7	10	
4503AD	17	Navy 84		3	9	6	10	
4506A	18	Navy 84		3	9	7+	10	
4505AD	18	Navy 84		3	10	6	10	
4510A	24	(4) 6		8	9	10	10	
4510AD	24	(4) 6		8	9+	9	10	

(4) 36.6% RL, 53.3% iron oxide, 9.9% Dicalite

INSPECTION RECORD - ATMOSPHERIC EXPOSURE

4" x 4" x 1/8" Angle Specimens

Wire Brushed - Solvent Cleaned

45° - South Exposure

Project No. 2
 Date Exposed 10/7/43
 Date Inspected 3/18/48
 Elapsed Time 53 months

Panel No.	Paint No.	How		One Coat Primer Area		Two Coat Primer Area		Comments
		P.	V.	Edge	Gen.	Edge	Gen.	
L856A	37	18	27	7	10	10	10	1st Choice of Series
L850A	35	16	19	7	10	10	10	2nd Choice of Series
L858A	38	16	14	6	10	9	10	3rd Choice of Series
L838A	30	6	5	1	10	6	10	
L840A	31	6	18	4	9	4	9	
L842A	32	5	14	4	10	10	9	
L844A	33	16	26	6	10	10	10	
L848A	34	16	27	4	10	10	10	
L851A	36	16	28	5	10	10	10	
L862A	39	19	14	1	10	10	10	
L866A	40	20	19	3	10	10	10	
L868A	41	20	28	2	10	10	10	
L870A	USMC XXII	1	1	2	10	8	10	
L874A	52-P-18	2	2	4	10	8	10	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
2 1/2 Feet Above High Tide
Flat Specimens

Project No. 3
Date Exposed 10/13/44
Date Inspected 3/18/48
Elapsed Time 41 months

Panel No.	Paint No.	New		Corrosion		Blistering	Chalking or Eroding	Comments
		P.	V.	Edge	Gen.			
L55A	34a	16	27	7	9	10	9/	1st Choice of Series
L13A	30	6	5	7	9/	9/	9/	2nd Choice of Series
L12A	45	72	19b	5	8/	10	9/	Top Coat Blistering Slightly
L14A	47	72	19d	6	8	10	9/	3rd Choice of Series
L60A	37a	18	27	6	8	10	9/	4th Choice of Series
L58A	56	20	27	5	9	10	9/	5th Choice of Series
L16A	52-P-18 Zn. Chrom. Primer	5	8	5	8	10	9/	6th Choice of Series
L11A	33	16	26	2	5		9/	7th Choice of Series
L15A	35	16	19	5	8		9/	
L16A	33a	16	26	4	7	10	9/	
L17A	33b	16	26	4	7	10	9/	
L18A	33c	16	26	5	7	10	9/	
L19A	33d	16	26	4	7	10	9/	
L20A	35a	16	19	2	7	10	9/	
L21A	35b	16	19	1	4	10	9/	
L22A	35c	16	19	2	5	10	9/	
L23A	35d	16	19	4	7	10	9/	
L24A	36a	16	28	3	8	10	9/	
L25A	36b	16	28	3	7	10	9/	
L26A	36c	16	28	4	6	10	9/	
L27A	36d	16	28	4	6	10	9/	
L28A	40a	20	19	1	3	10	9/	
L29A	40b	20	19	2	6	10	9/	
L30A	40c	20	19	2	6	10	9/	
L31A	40d	20	19	2	5	10	9/	
L32A	41a	20	28	4	7	10	9/	
L33A	41b	20	28	4	7	10	9/	
L34A	41c	20	28	4	7	10	9/	
L35A	41d	20	28	4	7	10	9/	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
2 1/2 Feet Above High Tide
Flat Specimens

Project No. 3
Date Exposed 10/13/44
Date Inspected 3/10/48
Elapsed Time 41 months

Panel No.	Paint No.	New		Corrosion		Blistering	Chalking or Eroding	Comments
		P.	V.	Edge	Gen.			
436A	42a	20	26	3	7	10	9%	
437A	42b	20	26	3	5	10	9%	
438A	42c	20	26	1	5	10	9%	
439A	42d	20	26	1	6	10	9%	
440A	40e	72	19	4	7	10	9%	
441A	44	72	19a	4	7	10	9%	
442A	46	72	19a	6	7	10	9%	
447A	48	72	19a	2	5	10	9%	
445A	USMC Class XIT 52-4-1			1	4	10	9%	
449A	49	16	19a	2	5	10	9%	
450A	50	16	19b	0	3	10	9%	
451A	51	16	19a	0	3	10	9%	
452A	52	16	19a	3	5	10	9%	
455A	54	16	27a	2	3	10	9%	
456A	55	16	26b	3	6	10	9%	
457A	53	16	26a	1	5	10	9%	
448A				3	6	10	9%	
453A				1	6	10	9%	
454A				2	6	10	9%	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
2 1/2 Feet Above High Tide
Flat Specimens

Page No. 1

Project No. 4
Date Exposed 10/13/41
Date Inspected 3/19/48
Elapsed Time 41 months

Panel No.	Paint No.	New		Corrosion		Blistering	Chalking or Eroding	Comments
		P.	V.	Edge	Gen.			
L68A	116	26	27	8	10	10	9/	1st Choice of Series
L95A	153	36	19	8	10	10	9/	2nd Choice of Series
L84A	132	42	27	7	9/	10	9/	3rd Choice of Series
L90A	138	46	27	7	9/	10	9/	4th Choice of Series
L72A	120	28	27	7	9	10	9/	5th Choice of Series
L69A	117	27	19	6	8	10	9/	
L70A	118	27	27	7	9	10	9/	
L71A	119	28	19	6	8	10	9/	
L73A	121	32	19	5	8	10	9/	
L74A	122	32	27	4	6	10	9/	
L75A	123	33	19	3	4	10	9/	
L76A	124	33	27	5	7	10	9/	
L77A	125	34	19	4	7	10	9/	
L78A	126	34	27	6	7	10	9/	
L79A	127	39	19	2	3	10	9/	
L80A	128	39	27	7	7	10	9/	
L81A	129	41	19	0	2	10	9/	
L82A	130	41	27	7	2/	10	9/	
L83A	131	42	19	3	6	10	9/	
L85A	133	43	19	3	6	10	9/	
L86A	134	43	27	6	8	9	9/	
L87A	135	45	19	7	8	10	9/	
L88A	136	45	27	6	7	10	9/	
L89A	137	46	19	1	5	10	9/	
L91A	179	29	19	4	5	10	9/	
L92A	180	30	19	7	8	10	9/	
L93A	181	31	19	3	5	10	9/	
L94A	182	35	19	2	6	10	9/	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
 2 1/2 Feet Above High Tide. BR 9432 Vs. Dyphens 13080
 Flat Specimens

Project No. 7a
 Date Exposed 10/23/44
 Date Inspected 3/1/45
 Elapsed Time 41 months

Panel No.	Paint No.	How		Edge	Gen.	Blistering	Chalking or Eroding	Comments
		P.	V.					
461A	97	16	20	2	5	10	9/	
462A	98	16	52	2	5	10	9/	
463A	99	71	19	3	6	10	9/	
464A	100	71	52	2	5	10	9/	
465A	101	71	19	2	4	10	9/	
466A	102	16	19	0	3	10	9/	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
2 1/2 Feet Above High Tide
Flat Specimens

Project No. 7b
Date Exposed 10/13/51
Date Inspected 11-14-51
Elapsed Time 41 months

Panel No.	Paint No.	Rise		Edge	Cen.	Blistering	Chalking or Eroding	Comments
		P.	V.					
498A	94	16	41	7	9	10	9/	First Panel of Series
496A	93	16	40	0	4	10	9/	
497A	94c	16	19	0	4	10	9/	
499A	95	16	42	5	8	10	9/	
500A	96	16	43	7	9	2	9/	Primer Plainly Visible
501A	33c	16	40	1	4	10	9/	
*502A	USMC XIII7	S2-A-1	S2-A-1	2	5	10	9/	
*503A	S2-P-18			3	6/	10	9/	
*504A	S2-MC-23			1	7	10	9/	
*505A	S2-MC-29			4	8	10	9/	

*Standards for Projects Nos. 3, 4 and 7.

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
Bakelite Vehicles. Angle Specimens.
45° - South Exposure

Page No. 3

Project No. 7c

Date Exposed 10/13/41

Date Inspected 3/18/48

Elapsed Time 41 months

Panel No.	Paint No.	New		One Coat Primer Area Corrosion		Two Coat Primer Area Corrosion		Comments
		P.	V.	Edge	Gen.	Edge	Gen.	
220A	86a	85	64	10	10	10	10	1st Choice of Series
230A	89	85	63	10	10	10	10	2nd Choice of Series
222A	85	88	51	8	10	10	10	3rd Choice of Series
213A	75	88	44	4	10	10	10	
214A	76	88	37	5	10	10	10	
215A	77	88	45	5	10	10	10	
216A	78	88	46	5	10	8	10	
217A	79	88	47	6	10	9	10	
218A	80	88	48	3	10	9	10	
219A	81	88	35	2	10	5	10	
220A	82	88	49	5	10	10	10	
221A	84	88	50	5	10	10	10	
223A	86	88	36	6	10	10	10	
224A	87	85	63	6	10	9	10	
225A	87a	85	63	2	6	5	7	
226A	87b	85	63	6	10	9	10	
227A	88	85	64	4	10	9	10	
229A	88b	85	64	5	10	9	10	
231A	90	85	64	6	10	10	10	
232A	52-W-29			4	10	10	10	
233A	52-WC-23			3	9	9	10	
234A	52-P-18			6	10	10	10	
235A	6	16	19	4	10	8	10	
236A	4	16	26	3	10	8	10	
237A	37	13	27	4	10	9	10	

L. I. A. PROJECT NO. 10Painting DiagramGalvanized Iron

6 2 Primer 1 Top Coat	3 1 Primer 1 Top Coat
5 2 Primer	2 1 Primer
4 Chemical Treat. 2 Primer	1 Chemical Treat. 1 Primer

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRON

Page No. 1

Project No. 10
 Date Exposed 6/25/46
 Date Inspected 3/18/48
 Elapsed Time 21 months

Panel No.	Paint No.	P.	V.	Peeling	Comments
1622-1	164	88	85	10	Unweathered - Lithoform
1623-1	.	.	.	10	
1624-1	.	.	.	6	
1625-1	.	.	.	10	Lithoform
1626-1	.	.	.	10	
1627-1	.	.	.	3	
1628-1	.	.	.	10	Unweathered - Copper Sulfate
1629-1	.	.	.	10	
1630-1	.	.	.	9	
1631-1	.	.	.	10	Copper Sulfate
1632-1	.	.	.	10	
1633-1	.	.	.	4	
1634-1	.	.	.	10	Weathered 6 No. - Lithoform
1635-1	.	.	.	10	
1636-1	.	.	.	10	
1637-1	.	.	.	10	Weathered 6 No. - Lithoform
1638-1	.	.	.	10	
1639-1	.	.	.	10	
1640-1	.	.	.	10	Weathered 9 No. - Lithoform
1641-1	.	.	.	10	
1642-1	.	.	.	10	
1643-1	.	.	.	10	Lithoform
1644-1	.	.	.	10	
1645-1	.	.	.	10	
1646-1	165	89	86	10	Unweathered - Lithoform
1647-1	.	.	.	10	
1648-1	.	.	.	10	
1649-1	.	.	.	10	Lithoform
1650-1	.	.	.	7	
1651-1	.	.	.	10	Unweathered - Copper Sulfate
1652-1	.	.	.	10	
1653-1	.	.	.	10	
1654-1	.	.	.	10	Copper Sulfate
1655-1	.	.	.	10	
1656-1	.	.	.	4	
1657-1	.	.	.	10	Weathered 6 No. - Lithoform
1658-1	.	.	.	10	
1659-1	.	.	.	10	
1660-1	.	.	.	10	Lithoform
1661-1	.	.	.	10	
1662-1	.	.	.	10	
1663-1	.	.	.	10	Weathered 6 No. - Copper Sulfate
1664-1	.	.	.	10	
1665-1	.	.	.	10	
1666-1	.	.	.	10	Copper Sulfate
1667-1	.	.	.	10	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRONPage No. 2

Project No. 10
 Date Exposed 6/25/45
 Date Inspected 3/15/48
 Elapsed Time 21 months

Panel No.	Paint No.	P.	V.	Feeling	Comments
1630-1	165	89	86	10	Weathered 9 Mo. - Lithoform
1630-2	.	.	.	10	
1630-3	.	.	.	10	
1630-4	.	.	.	10	
1630-5	.	.	.	10	
1630-6	.	.	.	10	
1630-7	.	.	.	10	
1630-8	.	.	.	10	
1630-9	.	.	.	10	
1630-10	.	.	.	10	
1630-11	.	.	.	10	
1630-12	.	.	.	10	
1630-13	.	.	.	10	
1630-14	.	.	.	10	
1630-15	.	.	.	10	
1630-16	.	.	.	10	
1630-17	.	.	.	10	
1630-18	.	.	.	10	
1630-19	.	.	.	10	
1630-20	.	.	.	10	
1630-21	.	.	.	10	
1630-22	.	.	.	10	
1630-23	.	.	.	10	
1630-24	.	.	.	10	
1630-25	.	.	.	10	
1630-26	.	.	.	10	
1630-27	.	.	.	10	
1630-28	.	.	.	10	
1630-29	.	.	.	10	
1630-30	.	.	.	10	
1630-31	.	.	.	10	
1630-32	.	.	.	10	
1630-33	.	.	.	10	
1630-34	.	.	.	10	
1630-35	.	.	.	10	
1630-36	.	.	.	10	
1630-37	.	.	.	10	
1630-38	.	.	.	10	
1630-39	.	.	.	10	
1630-40	.	.	.	10	
1630-41	.	.	.	10	
1630-42	.	.	.	10	
1630-43	.	.	.	10	
1630-44	.	.	.	10	
1630-45	.	.	.	10	
1630-46	.	.	.	10	
1630-47	.	.	.	10	
1630-48	.	.	.	10	
1630-49	.	.	.	10	
1630-50	.	.	.	10	
1630-51	.	.	.	10	
1630-52	.	.	.	10	
1630-53	.	.	.	10	
1630-54	.	.	.	10	
1630-55	.	.	.	10	
1630-56	.	.	.	10	
1630-57	.	.	.	10	
1630-58	.	.	.	10	
1630-59	.	.	.	10	
1630-60	.	.	.	10	
1630-61	.	.	.	10	
1630-62	.	.	.	10	
1630-63	.	.	.	10	
1630-64	.	.	.	10	
1630-65	.	.	.	10	
1630-66	.	.	.	10	
1630-67	.	.	.	10	
1630-68	.	.	.	10	
1630-69	.	.	.	10	
1630-70	.	.	.	10	
1630-71	.	.	.	10	
1630-72	.	.	.	10	
1630-73	.	.	.	10	
1630-74	.	.	.	10	
1630-75	.	.	.	10	
1630-76	.	.	.	10	
1630-77	.	.	.	10	
1630-78	.	.	.	10	
1630-79	.	.	.	10	
1630-80	.	.	.	10	
1630-81	.	.	.	10	
1630-82	.	.	.	10	
1630-83	.	.	.	10	
1630-84	.	.	.	10	
1630-85	.	.	.	10	
1630-86	.	.	.	10	
1630-87	.	.	.	10	
1630-88	.	.	.	10	
1630-89	.	.	.	10	
1630-90	.	.	.	10	
1630-91	.	.	.	10	
1630-92	.	.	.	10	
1630-93	.	.	.	10	
1630-94	.	.	.	10	
1630-95	.	.	.	10	
1630-96	.	.	.	10	
1630-97	.	.	.	10	
1630-98	.	.	.	10	
1630-99	.	.	.	10	
1630-100	.	.	.	10	
1630-101	.	.	.	10	
1630-102	.	.	.	10	
1630-103	.	.	.	10	
1630-104	.	.	.	10	
1630-105	.	.	.	10	
1630-106	.	.	.	10	
1630-107	.	.	.	10	
1630-108	.	.	.	10	
1630-109	.	.	.	10	
1630-110	.	.	.	10	
1630-111	.	.	.	10	
1630-112	.	.	.	10	
1630-113	.	.	.	10	
1630-114	.	.	.	10	
1630-115	.	.	.	10	
1630-116	.	.	.	10	
1630-117	.	.	.	10	
1630-118	.	.	.	10	
1630-119	.	.	.	10	
1630-120	.	.	.	10	
1630-121	.	.	.	10	
1630-122	.	.	.	10	
1630-123	.	.	.	10	
1630-124	.	.	.	10	
1630-125	.	.	.	10	
1630-126	.	.	.	10	
1630-127	.	.	.	10	
1630-128	.	.	.	10	
1630-129	.	.	.	10	
1630-130	.	.	.	10	
1630-131	.	.	.	10	
1630-132	.	.	.	10	
1630-133	.	.	.	10	
1630-134	.	.	.	10	
1630-135	.	.	.	10	
1630-136	.	.	.	10	
1630-137	.	.	.	10	
1630-138	.	.	.	10	
1630-139	.	.	.	10	
1630-140	.	.	.	10	
1630-141	.	.	.	10	
1630-142	.	.	.	10	
1630-143	.	.	.	10	
1630-144	.	.	.	10	
1630-145	.	.	.	10	
1630-146	.	.	.	10	
1630-147	.	.	.	10	
1630-148	.	.	.	10	
1630-149	.	.	.	10	
1630-150	.	.	.	10	
1630-151	.	.	.	10	
1630-152	.	.	.	10	
1630-153	.	.	.	10	
1630-154	.	.	.	10	
1630-155	.	.	.	10	
1630-156	.	.	.	10	
1630-157	.	.	.	10	
1630-158	.	.	.	10	
1630-159	.	.	.	10	
1630-160	.	.	.	10	
1630-161	.	.	.	10	
1630-162	.	.	.	10	
1630-163	.	.	.	10	
1630-164	.	.	.	10	
1630-165	.	.	.	10	
1630-166	.	.	.	10	
1630-167	.	.	.	10	
1630-168	.	.	.	10	
1630-169	.	.	.	10	
1630-170	.	.	.	10	
1630-171	.	.	.	10	
1630-172	.	.	.	10	
1630-173	.	.	.	10	
1630-174	.	.	.	10	
1630-175	.	.	.	10	
1630-176	.	.	.	10	
1630-177	.	.	.	10	
1630-178	.	.	.	10	
1630-179	.	.	.	10	
1630-180	.	.	.	10	
1630-181	.	.	.	10	
1630-182	.	.	.	10	
1630-183	.	.	.	10	
1630-184	.	.	.	10	
1630-185	.	.	.	10	
1630-186	.	.	.	10	
1630-187	.	.	.	10	
1630-188	.	.	.	10	
1630-189	.	.	.	10	
1630-190	.	.	.	10	
1630-191	.	.	.	10	
1630-192	.	.	.	10	
1630-193	.	.	.	10	
1630-194	.	.	.	10	
1630-195	.	.	.	10	
1630-196	.	.	.	10	
1630-197	.	.	.	10	
1630-198	.	.	.	10	
1630-199	.	.	.	10	
1630-200	.	.	.	10	
1630-201	.	.	.	10	
1630-202	.	.	.	10	
1630-203	.	.	.	10	
1630-204	.	.	.	10	
1630-205	.	.	.	10	
1630-206	.	.	.	10	
1630-207	.	.	.	10	
1630-208	.	.	.	10	
1630-209	.	.	.	10	
1630-210	.	.	.	10	
1630-211	.	.	.	10	
1630-212	.	.	.	10	
1630-213	.	.	.	10	
1630-214	.	.	.	10	
1630-215	.	.	.	10	
1630-216	.	.	.	10	
1630-217	.	.	.	10	
1630-218	.	.	.	10	
1630-219	.	.	.	10	
1630-220	.	.	.	10	
1630-221	.	.	.	10	
1630-222	.	.	.	10	
1630-223	.	.	.	10	
1630-224	.	.	.	10	
1630-225	.	.	.	10	
1630-226	.	.	.	10	
1630-227	.	.	.	10	
1630-228	.	.	.	10	
1630-229	.	.	.	10	
1630-230	.	.	.	10	
1630-231	.	.	.	10	
1630-232	.	.	.	10	
1630-233	.	.	.	10	
1630-234	.	.	.	10	
1630-235	.	.	.	10	
1630-236	.	.	.	10	
1630-237	.	.	.	10	
1630-238	.	.	.	10	
1630-239	.	.	.	10	
1630-240	.	.	.	10	
1630-241	.	.	.	10	
1630-242	.	.	.	10	
1630-243	.	.	.	10	
1630-244	.	.	.	10	
1630-245	.	.	.	10	
1630-246	.	.	.	10	
1630-247	.	.	.	10	
1630-248	.	.	.	10	
1630-249	.	.	.	10	
1630-250	.	.	.	10	
1630-251	.	.	.	10	
1630-252	.	.	.	10	
1630-253	.	.	.	10	
1630-254	.	.	.	10	
1630-255	.	.	.	10	
1630-256	.	.	.	10	
1630-257	.	.	.	10	
1630-258	.	.	.	10	
1630-259	.	.	.	10	
1630-260	.	.	.	10	
1630-261	.	.	.	10	
1630-262	.	.	.	10	
1630-263	.	.	.	10	
1630-264	.	.	.	10	
1630-265	.	.	.	10	
1630-266	.	.	.	10	
1630-267	.	.	.	10	
1630-268	.	.	.	10	
1630-269	.	.	.	10	
1630-270	.	.	.	10	
1630-271	.	.	.	10	
1630-272	.	.	.	10	
1630-273	.	.	.	10	
1630-274	.	.	.	10	
1630-275	.	.	.	10	
1630-276	.	.	.	10	
1630-277	.	.	.	10	
1630-278	.	.	.	10	
1630-279	.	.	.	10	
1630-280	.	.	.	10	
1630-281	.	.	.	10	
1630-282	.	.	.	10	
1630-283	.	.	.	10	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRONPage No. 3

Project No. 10
 Date Exposed 6/25/46
 Date Inspected 3/18/48
 Elapsed Time 21 months

Panel No.	Paint No.	Rus		Peeling	Comments
		P.	V.		
1638-1	167	16	4	10	Weathered 9 No. - Lithoform
1638-2	"	"	"	10	"
1638-3	"	"	"	10	"
1638-4	"	"	"	10	"
1638-5	"	"	"	10	Weathered 9 No. - Lithoform
1638-6	"	"	"	10	"
1638-7	"	"	"	10	"
1639-1	168	90	4	10	Unweathered - Lithoform
1639-2	"	"	"	10	"
1639-3	"	"	"	0	"
1639-4	"	"	"	10	Lithoform
1639-5	"	"	"	10	"
1639-6	"	"	"	2	"
1640-1	"	"	"	10	Unweathered - Copper Sulfate
1640-2	"	"	"	10	"
1640-3	"	"	"	1	"
1640-4	"	"	"	10	Copper Sulfate
1640-5	"	"	"	10	"
1640-6	"	"	"	1	"
1641-1	"	"	"	10	Weathered 6 No. - Lithoform
1641-2	"	"	"	10	"
1641-3	"	"	"	10	"
1641-4	"	"	"	10	Lithoform
1641-5	"	"	"	10	"
1641-6	"	"	"	10	"
1642-1	"	"	"	10	Weathered 6 No.-Copper Sulfate
1642-2	"	"	"	10	"
1642-3	"	"	"	10	"
1642-4	"	"	"	10	Copper Sulfate
1642-5	"	"	"	10	"
1642-6	"	"	"	10	"
1643-1	"	"	"	10	Weathered 9 No. - Lithoform
1643-2	"	"	"	10	"
1643-3	"	"	"	10	"
1643-4	"	"	"	10	Lithoform
1643-5	"	"	"	10	"
1643-6	"	"	"	10	"
1644-1	"	"	"	10	Weathered 9 No.-Copper Sulfate
1644-2	"	"	"	10	"
1644-3	"	"	"	10	"
1644-4	"	"	"	10	Copper Sulfate
1644-5	"	"	"	10	"
1644-6	"	"	"	10	"
1645-1	170	92	88	10	Unweathered - Lithoform
1645-2	"	"	"	10	"
1645-3	"	"	"	10	"
1645-4	"	"	"	10	"
1645-5	"	"	"	10	Lithoform
1645-6	"	"	"	10	"

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRONPage No. 4

Project No. 10
 Date Exposed 6/25/46
 Date Inspected 3/18/48
 Elapsed Time 21 months

Panel No.	Paint No.	How		Peeling	Comments
		P.	V.		
1646-1	170	92	88	10	Unweathered - Copper Sulfate
1646-2	"	"	"	10	
1646-3	"	"	"	10	
1646-4	"	"	"	10	Copper Sulfate
1646-5	"	"	"	10	
1646-6	"	"	"	10	
1647-1	"	"	"	10	Weathered 6 Mo. - Lithoform
1647-2	"	"	"	10	
1647-3	"	"	"	10	
1647-4	"	"	"	10	Lithoform
1647-5	"	"	"	10	
1648-1	"	"	"	10	Weathered 9 Mo. - Lithoform
1648-2	"	"	"	10	
1648-3	"	"	"	10	
1648-4	"	"	"	10	Lithoform
1648-5	"	"	"	10	
1649-1	171	92	172	10	Unweathered - Lithoform
1649-2	"	"	"	10	
1649-3	"	"	"	10	
1649-4	"	"	"	10	Lithoform
1649-5	"	"	"	10	
1650-1	"	"	"	10	Unweathered - Copper Sulfate
1650-2	"	"	"	10	
1650-3	"	"	"	10	
1650-4	"	"	"	10	Copper Sulfate
1650-5	"	"	"	10	
1651-1	"	"	"	10	Weathered 6 Mo. - Lithoform
1651-2	"	"	"	10	
1651-3	"	"	"	10	
1651-4	"	"	"	10	Lithoform
1651-5	"	"	"	10	
1652-1	"	"	"	10	Weathered 9 Mo. - Lithoform
1652-2	"	"	"	10	
1652-3	"	"	"	10	
1652-4	"	"	"	10	Lithoform
1652-5	"	"	"	10	
1653-1	172	138	173	10	Unweathered - Lithoform
1653-2	"	"	"	10	
1653-3	"	"	"	10	
1653-4	"	"	"	10	
1653-5	"	"	"	10	Lithoform

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRONPage No. 5

Project No. 10
 Date Exposed 6/25/46
 Date Inspected 3/18/48
 Elapsed Time 21 months

Panel No.	Paint No.	New		Peeling	Comments
		P.	V.		
1654-1	272	138	173	10	Unweathered - Copper Sulfate
1654-2	"	"	"	10	
1654-3	"	"	"	10	
1654-4	"	"	"	10	Copper Sulfate
1654-5	"	"	"	10	
1654-6	"	"	"	10	
1655-1	"	"	"	10	Weathered 6 Mo. - Lithoform
1655-2	"	"	"	10	
1655-3	"	"	"	10	
1655-4	"	"	"	10	Lithoform
1655-5	"	"	"	10	
1655-6	"	"	"	10	
1656-1	"	"	"	10	Weathered 9 Mo. - Lithoform
1656-2	"	"	"	10	
1656-3	"	"	"	10	
1656-4	"	"	"	10	Lithoform
1656-5	"	"	"	10	
1656-6	"	"	"	10	
1657-1	273	139	174	10	Unweathered - Lithoform
1657-2	"	"	"	10	
1657-3	"	"	"	10	
1657-4	"	"	"	10	Lithoform
1657-5	"	"	"	10	
1657-6	"	"	"	10	
1658-1	"	"	"	10	Unweathered - Copper Sulfate
1658-2	"	"	"	10	
1658-3	"	"	"	10	
1658-4	"	"	"	10	Copper Sulfate
1658-5	"	"	"	10	
1658-6	"	"	"	10	
1659-1	"	"	"	10	Weathered 6 Mo. - Lithoform
1659-2	"	"	"	10	
1659-3	"	"	"	10	
1659-4	"	"	"	10	Lithoform
1659-5	"	"	"	10	
1659-6	"	"	"	10	
1660-1	"	"	"	10	Weathered 6 Mo. - Copper Sulfate
1660-2	"	"	"	10	
1660-3	"	"	"	10	
1660-4	"	"	"	10	Copper Sulfate
1660-5	"	"	"	10	
1660-6	"	"	"	10	
1661-1	"	"	"	10	Weathered 9 Mo. - Lithoform
1661-2	"	"	"	10	
1661-3	"	"	"	10	
1661-4	"	"	"	10	Lithoform
1661-5	"	"	"	10	
1661-6	"	"	"	10	

INSPECTION RECORD - ATMOSPHERIC EXPOSURE
GALVANIZED IRONPage No. 6

Project No. 10
 Date Exposed 6/25/46
 Date Inspected 3/18/48
 Elapsed Time 21 Months

Panel No.	Paint No.	New		Peeling	Comments
		P.	V.		
1662-1	273	139	174	10	Weathered 9 Mo. - Copper Sulfate
1662-2	"	"	"	10	
1662-3	"	"	"	10	
1662-4	"	"	"	10	Copper Sulfate
1662-5	"	"	"	10	
1662-6	"	"	"	10	
1663-1	274	40	175	10	Unweathered - Lithoform
1663-2	"	"	"	10	
1663-3	"	"	"	10	Lithoform
1663-4	"	"	"	10	
1663-5	"	"	"	10	
1663-6	"	"	"	10	Unweathered - Copper Sulfate
1663-7	"	"	"	10	
1663-8	"	"	"	10	Copper Sulfate
1663-9	"	"	"	10	
1663-10	"	"	"	10	
1665-1	"	"	"	10	Weathered 6 Mo. - Lithoform
1665-2	"	"	"	10	
1665-3	"	"	"	10	
1665-4	"	"	"	10	Lithoform
1665-5	"	"	"	10	
1665-6	"	"	"	10	
1665-7	"	"	"	10	Weathered 9 Mo. - Lithoform
1665-8	"	"	"	10	
1665-9	"	"	"	10	Lithoform
1665-10	"	"	"	10	
1667-1	Class XXII	QDR	"	10	Unweathered - Lithoform
1667-2	"	"	"	10	
1667-3	"	"	"	10	
1667-4	"	"	"	10	Lithoform
1667-5	"	"	"	10	
1667-6	"	"	"	10	
1668-1	"	"	"	10	Unweathered - Lithoform
1668-2	"	"	"	10	
1668-3	"	"	"	10	
1668-4	"	"	"	10	Lithoform
1668-5	"	"	"	10	

*Fig 1 R.L. 56.5, Mg. 81.1, 23.4, Fe₂O₃ 1.3, Zn. Yellow 9.9, Mica 8.6,
 Al. Stear. 0.3

Veh: 24.5 G.E. 2529
 36.4 G.E. 2454
 16.8 33 gal. Tung BRL329 Var.
 22.3 Thinner & Driers.