VISCOSITY WORK SHEET

Item 3119 P.T.No. Date 11-10-55

Worker Kay - STANLEY Polymer Lucite Solvent EDC

For CAMERON Charge 1290 Temperature 25°C.

Viscometer No. C Efflux Time 204.2, 204.4, 204.3 Weight: Gross 4751.0

Viscometer No. Efflux Time Tare 4.625.

Viscometer No. Efflux Time Net 0.125.

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. visc. or M.W.
4819-128-S	TT	C	259.8; 259.5; 259.7	1.271	118,500

PC-1

11-11-55