

DISTRIBUTION:

R. Mack
R. Burks
J. Kozdron
M. Collins
K. Patel
R. Smith (4)
J. Latsko
ROUTE: MS, RR, JT, TK

AIRFLEX TEST REQUEST

DATE October 6, 1983 REQUESTED BY J. Latsko

TEST DESCRIPTION FRICTION MATERIAL SCREENING FOR CB APPLICATIONS

TEST STAND FMTM PART NUMBER/S

PARTS LIST Y OR Z NUMBER Y0259-3

1.0 PREFACE:

Because of the potential health hazards associated with asbestos, including the possibility of additional government controls and/or regulations, and including increasing numbers of customer requests for non-asbestos linings, it is desirable/required to eliminate the use of asbestos in our friction materials.

2.0 OBJECTIVE:

The objective of this test is to qualify non-asbestos friction materials for normal CB usage.

3.0 INSTRUCTIONS:

Using materials submitted by the writer, perform automatic drum driveline deceleration tests per the following:

Drum test temperatures: 100°F (wear-in thru stabilization),
200°F, 300°F, 400°F, 100°F, 200°F (wear-test).

Drum test speed: 3000 FPM initial velocity.

Test stand inertia: 60 lb.-ft.²

Applied pressure: 75 PSI

Jim Latsko

JL:jo