

32

CODE

CODE **R7698**

LOT

K2J-19

LOCATION

24

231

26

STUMP

TOTAL NET WT.

2311

LUMP WT:

2336

PKG. N-CODE

PROD. SUPV.

DATE _____

DATE 10/12/82

OPERATOR

OPERATOR
22

0.0

0.88 +
0.85 +
1.03 +
0.88 +
0.97 +
0.88 +
0.85 +
1.03 +
0.95 +
0.99 +
1.03 +
1.11 +
0.96 +
0.96 +
1.13 +
0.97 +
0.96 +
0.92 +
1.01 +
0.97 +
0.99 +
0.90 +
0.94 +
0.95 +

024

23.11

PRODUCT NAME: WATCHUNG RED B

NON-BLEEDING

CG 32 CODE RT-698-D PKG

PROCESSES APPROVED BY:

RT-698-D (0) EWR 03/02/82

LOT *A2379*

EST. WT. ~~*****~~ LBS.

2750

MAKING NOTES:

INSTRUCTIONS

= PRESSING =

RECORD

VAT		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		STARTED	10 PM				
TIME		CAKES USED	80				
RELEASED BY		WATER ON	5 PM				
PRESS	95	HRS. WASHED	7				
NO. OF CAKES	80	M MHOS	202				
PRESS WITH	AGITATION	HRS. WASHED					
WASH TO 333 M MHOS	35-75 DEG F WATER	M MHOS					
TEST AFTER 6 HOURS		HRS. WASHED					
LOAD ON 13 CARS		M MHOS					
CLEAN MAGNETIC SEPARATOR AFTER		CAKE CONDITION					
PRESSING.	CLEANED BY:	NO CARS LOADED	11				
TIME CLEANED:		EXPLAIN LOSSES					

SAMPLES JAR
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 12 HOURS AT 220 F
THEN DRY 12 HRS AT 200 DEG F. HOLD
ON TRACK FOR 30 MIN BEFORE DUMPING.

LUMP: - OK - WET - SALTS - CONTAMINATED

=====

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 78
LUMP WGT 2336

= GRINDING =

MILL 2 LSP 0.066" RP SCREEN 1800 RPM
MAX. TEMP. 140 DEG F
INERT MILL WITH CO2 WHEN GRINDING
PER O.P. #O.F. 0043.

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 ENV.
DELIVER TO CTL

DATE MIXED 10-12-82

SAMPLED BY 389
RELEASED BY

19
51
18

18 drum
23 36 4

1.44	+
0.14	- ✓
1.47	+
0.14	- ✓
1.40	+
0.14	- ✓
1.41	+
0.14	- ✓
1.39	+
0.14	- ✓
1.41	+
0.14	- ✓
1.37	+
0.14	- ✓
1.49	+
0.14	- ✓
1.56	+
0.14	- ✓
1.58	+
0.14	- ✓
1.47	+
0.14	- ✓
1.48	+
0.14	- ✓
1.41	+
0.14	- ✓
1.46	+
0.14	- ✓
1.38	+
0.14	- ✓
1.36	+
0.14	- ✓
1.42	+
0.14	- ✓
1.38	+
0.14	- ✓
23.36	*