MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky-787 LOT E1459

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	60	3000		
	STUMP	Lump 3378		

TOTAL NET WT. 3000 PKG. N–CODE 10800

PROD. SPVR. DATE WHSE. OPER.

5/27/80

DUP050096439

N31377

22/240

CG 03 CODE KY-787-D PKG. ____

→MAY -0·81- ~~[illegible]~~ E 1459

EST. WGT. ~~XXXX~~ 932 LBS.

O12/RP

Total Wgt. ~~3352#~~ ~~3514~~ 3464

PROCESSING INSTRUCTIONS: BATCH UN

PROCESSES	APPROVED
KY-787-D (R)	FWK 9/22/
Alternate	DCG 9/27/
TYPED BY	
NF 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	240				
DATE	5-18-81				
TIME	3:30 A.M.				
RELEASED BY	K.M.				
PRESS	22	23	24	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5T
STARTED	10 AM				
CAKE USED	46				
WATER ON	4 30 PM				
HRS. WASHED	8				
OHMS	3500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	6				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 13

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3378

SAMPLED BY RELEASED BY

-GRINDING-

MILL 999 HRP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES Unable To Give Reason For Low Yield N.G.

SAMPLE / WITHOUT MIXING

SAMPLES 1 PNV & 1 Pt. can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096440

1459
41
100

2.74	+
0.12	-
2.78	+
0.12	-
2.82	+
0.12	-
2.80	+
0.12	-
2.67	+
0.12	-
2.79	+
0.12	-
2.67	+
0.12	-
2.75	+
0.12	-
2.69	+
0.12	-
2.81	+
0.12	-
2.86	+
0.12	-
2.57	+
0.12	-
2.39	+
0.12	-
33.78	*

DUP050096441