

NAME: FULTON 4 HOUR ENAMEL
 CATEGORY: INTERIOR ENAMEL
 COLOR: WHITE
 NUMBER: 1085
 QUALITY: SECOND

SS.	GALS.			
		ment	26%	
7.5	2.09	Titanium Dioxide	.1475	9.956
.43	5.5	Titanox CX	06	8.590
52	1.48	Lithopone	045	2.340
		icle	74%	
17.5	16	Baking Varnish	62	9.920
03.9	54.25	White Enamel Liquid	742	40.254
24	32	Mixing Varnish	481	15.392
107.80	111.32			86.442
	4.45	- 4% Mfg. Loss		
	106.9	Material Cost per Gallon	-	.809
		Direct Labor Cost	-	.042
		Factory Overhead	-	.067
		Bulk Cost per Gallon	-	.918
		Complete Package Cost	-	.108
		Factory Cost in Package per Gallon	-	1.026