

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO H. B. Carr • AT Burlington DATE July 31, 1969
FROM E. L. Kanyok AT Burlington COPY TO J. C. Fisher
SUBJECT Mexican Gelatin File ✓
Project No.: 70-001

The samples of gelatin from Mexico have been received and tested. The following are the results obtained by Burlington Quality Control and how they compare to our specifications:

<u>Properties</u>	<u>275A</u>	<u>Mexico "A"</u>	<u>250B</u>	<u>Mexico "B"</u>
pH	4.2-4.8	4.6	5.4-6.5	4.2
Volatiles	11% max.	6.9	11% max.	4.1
Contamination	50% max.	17/0	50% max.	26/0
Screen 40	5% max.	46	5% max.	11

It is unknown whether the Mexican "A" and "B" samples are two different types of gelatin or two samples of the same type. By the above results, it appears to be the same type and compares to our 275A (Rozic) except for particle size.

E. L. Kanyok
E. L. Kanyok

ELK/rjl