

MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 907 LOT 37643

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2000	1	T-19		
1910	1	T-217		
1998	1	T-137		
	STUMP	LUMP	5808	

TOTAL NET WT. 5908 PKG. N--CODE

PROD. SPVR. DATE WHSE. OPER.

11/12/90

N34908

DUP050105771

95
262

CG 03 CODE KY-907-D PKG.

→ OCT·29 80 37643

EST. WGT. 1853 LBS.

OK
R

TOTAL WGT. 6053#

PROCESSING INSTRUCTIONS: BATCH UN

PROCESSES	APPROVED
KY-907-D (F)	FWK 12/12
Alternate	DCG 12/14
TYPED BY	
rj 2/8/77	

MAKING NOTES

REMARKS

AME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

EC INSTRUCTIONS -PRESSING- RECORD

AT	262					PRESSLOAD	1ST	2ND	3RD	4TH
ATE	10-30-80					STARTED	8			
IME	6:30 AM					CAKES USED	12			
ELEASED BY	S.B.					WATER ON	1P			
RESS	96	95				HRS. WASHED	3			
O OF CAKES	72	72				OHMS	2000			
RESS With		AGITATION				HRS. WASHED				
ASH TO 2000		OHMS with 135-145°F water				OHMS				
EST AFTER 3		HOURS				HRS. WASHED				
OAD on 10 cars						OHMS				
						CAKE CONDITION				
						NO. CARS LOADED	10			

EXPLAIN LOSSES

S3b

AMPLES 8oz Jar
ELIVER TO CTL for color

SAMPLED BY 499 RELEASED BY S3b

-DRYING-

RY 24 HOURS AT 180 °F

Dry on first stage only.

Re-pel every 5 hours til dry.

LUMP: - OK - WET - SALTS - CONTAMIN

NO more color in area no Record of any PROCESSING LOSS

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 23

MPLES

NO. CARS PULLED LUMP WGT. 5809

ELIVER TO

SAMPLED BY RELEASED BY Bbb

-GRINDING-

ILL 949 HSP 1/8" RP SCREEN 3500 RPM

AX TEMP 170°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

MPLE WITHOUT MIXING

MPLES 1 ENV & 1PT CAN

ELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105772



DUP050105773