106 Vat 17 @ 135°F

CG 46 CODE YC-11-A PKG. ____

→ NOV 26 80 37985

EST. WGT. [redacted] 1700 LBS.

Note: - Press lots 37984, 37985 simultaneously thru in line mixer into membrane press
- Wait for both lots before pressing

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(D) YC-11-A	EWK 9-28-76
	BBK 10-17-77
	DCG 11-29-77
TYPED BY	
JIC 12-8-77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

-PRESSING-

INSTRUCTIONS

VAT				106	
DATE				11-21-80	
TIME				830P	
RELEASED BY				8V	
PRESS	32	33	35	M1	
NO. OF CAKES	60	62	60		

PRESS WITHOUT AGITATION

WASH TO 4000 OHMS WITH 35-75°F WATER

TEST AFTER 4 HOURS

LOAD IN METAL DRUMS AT 325# NET PER DRUM

AIR BLOW PRESSCAKE 15 MIN AT 40PSI

SAMPLES THIEF SAMPLE & FILL 1-8 oz. jar + 1 qt each from north end, center, south end of press

DELIVER TO CTL for color

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1155 AM				
CAKES USED	62				
WATER ON	7 PM	—			
HRS. WASHED	5				
OHMS	4500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

DRY — HOURS AT — °F

DO NOT DRY

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

-GRINDING-

MILL SCREEN RPM

MAX. TEMP. °F

SAMPLE AFTER / WITHOUT MIXING

SAMPLES

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

N35273

DUP050108352