CG 40 CODE RT-160-P PKG. ____

→MAY-0-81 E 1133-1

EST. WGT. 665 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

| | PROCESSES | APPROVED BY |
|---|---|---|
| | RT-160-P (C) | BBK 04-26-77 |
| | | DCG 04-26-77 |
| | | BBK 03-22-79 |
| | TYPED BY | |
| | emw032679 | |

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED LIGHT

NON-BLEEDING

| INSTRUCTIONS | | | | | | -PRESSING- RECORD | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| YAT | 260 | | | | | PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
| DATE | 5/4/81 | | | | | STARTED | 9:30A | | | | |
| TIME | 9:00 Pm | | | | | CAKES USED | 36 | | | | |
| RELEASED BY | PMD | | | | | WATER ON | 1 PM | | | | |
| PRESS | 12 | 26 | | | | HRS. WASHED | 8 | | | | |
| NO. OF CAKES | 36 | 40 | | | | OHMS | 6000 | | | | |
| PRESS without AGITATION | | | | | | HRS. WASHED | | | | | |
| WASH TO 4000 OHMS with 35-75°F water | | | | | | OHMS | | | | | |
| TEST AFTER 2 HOURS | | | | | | HRS. WASHED | | | | | |
| LOAD in N-1775-A at 360# net per drum | | | | | | OHMS | | | | | |
| | | | | | | CAKE CONDITION | | | | | |
| | | | | | | NO. CARS LOADED | | | | | |
| | | | | | | EXPLAIN LOSSES | | | | | |

THIEF } 1 Pt for CTL &
SAMPLES } 1 Qt for Pre-Shipment

DELIVER TO CTL

SAMPLED BY TDS RELEASED BY

-DRYING-

| HOURS | L.V. | H.V. |
|---|---|---|
| | | |

LUMP: - OK - WET - SALTS - CONTAMINATED

Do Not Dry

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT.

RELEASED BY

-GRINDING-

| MILL | SCREEN | RPM |
|---|---|---|
| MAX. TEMP. | °F | |

| SCREEN | RPM |
|---|---|
| MAX. TEMP. | °F |

Do Not Grind

SAMPLE AFTER / WITHOUT MIXING

SAMPLES

DATE MIXED

RELEASED BY