

01 CODE YE-698-D PKG

LOT MAY -0-81-E-1434

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS				= PRESSING =	RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES	
292	5-19	1:50	JDC	2	92	93																	
				54	54	54																	

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =
(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED 8
SAMPLED BY
RELEASED BY

NO DRAWS
LUMP WGT 15028

= GRINDING =
MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1434
41
158

0.00 *
3.35 +
0.12 ✓
3.44 +
0.12 ✓
3.43 +
0.12 ✓
3.27 +
0.12 ✓
3.17 +
0.12 ✓
3.40 +
0.12 ✓
3.33 +
0.12 ✓
3.42 +
0.12 ✓
3.16 +
0.12 ✓
3.60 +
0.12 ✓
3.57 +
0.12 ✓
3.22 +
0.12 ✓
3.08 +
0.12 ✓
3.43 +
0.12 ✓
3.44 +
0.12 ✓
3.49 +
0.12 ✓
3.16 +
0.12 ✓
3.48 +
0.12 ✓
58.28 *