

Eagle Insulating Material

Taken from Geismar home. Received: April 15, 1938.

Analysis No. 38A-1685

Sample Taken - 1.00 gm
Mgs Total Lead - 9.4
% Total Lead - 0.94

Lead soluble in 0.25% HCl by weight according to
British Government Test.

Gms Taken - 1.00
Mgs Lead in
Filtrate - 3.10
% of Lead
Soluble - 33.0

*Test result should be
with confidence, the amount
3.9 at 4.0 is
remaining
Compare with 3.10 offered*

Lead soluble in 1% HCl, by weight.

Gms Taken - 1.00
Mgs Lead in
Filtrate - 7.0
% of Lead
soluble - 75.0

Reported: April 18, 1938

N9665

KE 0008298