

March 7, 1975
Formula C-972
NEW

CHICAGO, ILLINOIS, PLANT FORMULA
READY MIX FILLER C-972

DESCRIPTION OF PRODUCT - Filler for Ready Mix taping compound C-979.

<u>FORMULA</u>	<u>Function</u>	<u>RM Spec</u>	<u>Percent</u>	<u>Lbs/Batch</u>
Asbestos 7RF09	Bulking agent	9	4.25	170.00
Dowicil 75	Fungicide	193	.20	8.00
Gelvatol 6000	Adhesive	162	1.00	40.00
Gendriv 492S	Water retention aid	223	.85	34.00
Mica	Anti-cracking agent	11	9.50	380.00
Limestone	Filler	13	84.20	3368.00
			100.00	4000.00

WORKING CONSISTENCY
Specifications

- Refer to Plant Testing Procedure No. 32.

<u>Maximum</u>	<u>Minimum</u>	<u>Average</u>
57	53	55

WORKING PROPERTIES
Specifications

- Refer to Plant Testing Procedure No. 33
Filler shall be very heavily bodied and possess fair plasticity. It shall be free of any coarse, gritty, or undispersed particles.

COLOR
Specifications

- White
Dried compound shall match color of standard sample.

NOTE: A wet mix of the filler shall be prepared according to Formula No. C-979 at least twice a day or with every 6th or 7th batch of filler manufactured. This prepared mix shall be tested and shall meet all the specifications required of Ready Mix Joint Compound - Formula No. C-979.

WNG:elz

