

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Acetaldehyde	100%	O	U		
Acetic Acid (Glacial)	Conc.	O	U		
Acetic Anhydride		U	U		
Acetic Acid	1-10%	S	S		
Acetic Acid	10-60%	S	O		
Acetic Acid	80-100%	O	U		
Acetone		S	S	S	S
Acetone	100%	U	U		
Acrylic Emulsions		S	S	S	S
Allyl Alcohol		U	U		
Allyl Chloride		U	U		
Aluminum Chloride	Dilute	S	S	S	S
Aluminum Chloride	Conc.	S	S	S	S
Aluminum Fluoride	Conc.	S	S	S	S
Aluminum Hydroxide	Conc.	S	S		
Aluminum Sulfate	Conc.	S	S	S	S
Alums (all types)	Conc.	S	S	S	S
Ammonia	100% Dry Gas	S	S	S	S
Ammonium Carbonate		S	S	S	S
Ammonium Chloride	Sat'd	S	S	S	S
Ammonium Carbonate	Conc.	S	S		
Ammonium Chloride	Sat'd	S	S		
Ammonium Fluoride	20%	S	S	S	S
Ammonium Hydroxide		S	S	S	S
Ammonium Hydroxide	35%	S	S		
Ammonium Metaphosphate	Sat'd	S	S	S	S
Ammonium Nitrate	Sat'd	S	S	S	S
Ammonium Persulfate	Sat'd	S	S	S	S
Ammonium Persulfate	Sat'd	S	S		
Ammonium Sulfate	Sat'd	S	S	S	S
Ammonium Sulfide	Sat'd	S	S	S	S
Ammonium Thiocyanate	Sat'd	S	S		
Ammonium Thiocyanate	Sat'd	S	S	S	S
Amyl Acetate	100%	U	U	O	U
Amyl Alcohol	100%	S	S	S	S
Amyl Chloride	100%	U	U		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Aniline	100%	S	U	S	
Aniline Hydrochloride	Sat'd		U		
Antimony Chloride		U	U		U
Aqua Acid		U	U		
Aqua Regis		O	U	O	U
Arsenic Acid	100%	S	S		
Barium Carbonate	Sat'd	S	S	S	S
Barium Chloride	Sat'd	S	S	S	S
Barium Hydroxide	Sat'd	S	S		
Barium Sulfide	Sat'd	S	S	S	S
Beer		S	S	S	
Benzene		U	U	O	U
Benzene Sulfonic Acid		S	S	S	S
Benzoic Acid	Sat'd	O	O		
Benzoic Acid	All Conc.	S	S		
Benzene Sulfonic Acid		S	S		
Bismuth Carbonate	Sat'd	S	S	S	S
Black Liquor		S	S	S	S
Bleach Lye	10%	S	S	S	S
Borax	Sat'd	S	S		
Borax	Cold Sat'd	S	S		
Boric Acid	Conc.	S	S	S	S
Boric Acid	Dilute	S	S	S	S
Bromic Acid	10%	S	S		
Bromic Acid	100%	U	U		
Borax Cold	Sat'd	S	S	S	S
Bromic Acid	10%	S	S	S	S
Bromine Liquid	100%	U	U	O	U
Bromine Water		U	U		
Butanediol	100%	S	S		
Butanediol	60%	S	S		
Butanediol	10%	S	S		
Butyl Alcohol	100%	S	S		
Butyric Acid	Conc.	U	U		
Calcium Bisulfide		S	S	S	S

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Calcium Carbonate	Sat'd	S	S	S	S
Calcium Chlorate	Sat'd	S	S	S	S
Calcium Chloride	Sat'd	S	S	S	S
Calcium Hydroxide	Sat'd	S	S		
Calcium Hydroxide		S	S	S	S
Calcium Hypochlorite	Bleach Sol'n	S	S	S	S
Calcium Nitrate	Sat'd	S	S		
Calcium Nitrate	50%	S	S	S	S
Calcium Sulfate		S	S	S	S
Camphor Oil		U	U		
Carbon Dioxide	100% Dry	S	S	S	S
Carbon Dioxide	100% Wet	S	S	S	S
Carbon Dioxide	Cold Sat'd	S	S	S	S
Carbon Disulfide		U	U		
Carbon Disulphide		U	U		U
Carbon Monoxide		S	S	S	S
Carbon Tetrachloride		U	U	U	U
Carbonic Acid		S	S	S	S
Caster Oil	Conc.	S	S		
Chloracetic Acid	100%	U	U		
Chlorine Moist Gas		O	U		
Chlorine Liquid		U	U	O	U
Chlorine Water	2% Sat'd Sol	U	U		
Chlorobenzene		U	U	O	U
Chloroform	100%	U	U	U	U
Chlorosulfonic Acid		U	U	U	U
Chrome Alum	Sat'd	S	S	S	S
Chromic Acid	10-20%	S	O	S	O
Chromic Acid	20%	S	S		
Chromic Acid & Sulfuric Acid		S	O		
Chromic Acid	50%	S	O	S	O
Cider		S	S	S	S
Citric Acid	Sat'd	S	S	S	S
Coconut Oil Alcohols		S	S	S	S
Cola Concentrates		S	S		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Copper Chloride	Sat'd	S	S	S	S
Copper Cyanide	Sat'd	S	S		
Copper Fluoride	2%	S	S	S	S
Copper Nitrate	Sat'd	S	S	S	S
Copper Sulfate	Dilute	S	S	S	S
Copper Sulfate	Sat'd	S	S	S	S
Cottonseed Oil	100%	S	S		
Cottonseed Oil		S	S	S	S
Cresol	100%	U	U		
Cresylic Acid	50%	S	S		
Cuprous Chloride	Sat'd	S	S	S	S
Cyclohexane	100%	U	U		
Cyclohexanone		U	U	U	U
Cyclohexanol	100%	S	S		
Detergents, Synthetic		S	S	S	S
Developers Photographic		S	S	S	S
Dextrin	Sat'd	S	S	S	S
Dextrose	Sat'd	S	S	S	S
Diazo Salts		S	S		
Dibutylphthalate		O	O		
Diethylene Glycol	100%	O	U		
Diethylene Glycol		S	S	S	S
Diglycolic Acid		S	S		
Dimethylamine		U	U		
Diocetyl Phthalate		O	U		
Disodium Phosphate	Sat'd	S	S		
Emulsions, Photographic		S	S		
Ethyl Acetate	100%	O	O	O	O
Ethyl Alcohol	35%	S	S	S	S
Ethyl Alcohol	100%	S	S	S	S
Ethyl Butyrate	100%	O	U		
Ethyl Chloride		U	U	O	U
Ethyl Ether	100%	U	U		
Ethylene Chloride		U	U		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Ethylene Chlorohydrin		U	U		
Ethylene Dichloride		U	U		
Ethylene Glycol		S	S	S	S
Ferric Chloride	Sat'd	S	S	S	S
Ferric Nitrate	Sat'd	S	S	S	S
Ferric Sulfate	Sat'd	S	S		
Ferrous Chloride	Sat'd	S	S	S	S
Ferrous Sulfate		S	S	S	S
Fish Solubles		S	S		
Fluoboric Acid		S	S		
Fluorine		S	U		
Fluosilicic Acid	32%	S	S		
Fluosilicic Acid	Conc.	S	O		
Fluoboric Acid		S	S	S	S
Fluorine		S	U	S	U
Fluosilicic Acid	32%	S	S	S	S
Fluosilicic Acid	Conc.	S	O	S	S
Formaldehyde	40%	S	S	S	
Formic Acid	20%	S	S	S	S
Formic Acid	50%	S	S	S	S
Formic Acid	100%	S	S	S	S
Fructose	Sat'd	S	S	S	S
Fruit Pulp		S	S		
Fuel Oil		O	U	S	U
Furfural	100%	U	U	O	U
Furfuryl Alcohol		U	U		
Gallic Acid	Sat'd	S	S	S	S
Gasoline		U	S	U	
Gin		U	U		
Glucose		S	S	S	S
Glycerine		S	S	S	S
Glycol		S	S	S	S
Glycolic Acid	30%	S	S	S	S
Grape Sugar	Sat'd Aq.	S	S		
Heptane	100%	U	U		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Hydrobromic Acid	50%	S	S	S	S
Hydrocyanic Acid	Sat'd	S	S	S	S
Hydrochloric Acid	10%	S	S	S	S
Hydrochloric Acid	30%	S	S	S	S
Hydrochloric Acid	35%	S	S	S	S
Hydrochloric Acid	Conc.	S	S	S	S
Hydrofluoric Acid	40%	S	S	S	S
Hydrofluoric Acid	60%	S	S	S	S
Hydrofluoric Acid	75%	S	O	S	S
Hydrofluorosilicic	31.1%	S	S		
Hydrogen	100%	S	S	S	S
Hydrogen Bromide	10%	S	S	S	S
Hydrogen Chloride Gas	Dry	S	S	S	S
Hydrogen Peroxide	30%	S	O	S	S
Hydrogen Peroxide	90%	S	U	S	O
Hydrogen Phosphide	100%	S	S		
Hydrogen Sulfide		S	S	S	S
Hydroquinone		S	S	S	S
Hypochlorous Acid	Conc.	S	S	S	S
Inks		S	S	S	S
Iodine (in KI Sol'n)		O	U		
Lactic Acid	10%	S	S	S	S
Lactic Acid	90%	S	S	S	S
Lead Acetate	Sat'd	S	S	S	S
Latex	100%	S	S		
Lead Acetate	Sat'd	S	S		
Lead Tetra-Ethyle	100%	S			
Linseed Oil		O	U		
Lube Oil		O	U		
Magnesium Carbonate	Sat'd	S	S	S	S
Magnesium Chloride	Sat'd	S	S	S	S
Magnesium Hydroxide	Sat'd	S	S	S	S

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Magnesium Nitrate	Sat'd	S	S	S	S
Magnesium Sulfate	Sat'd	S	S	S	S
Maleic Acid	Sat'd	S	S		
Mercuric Chloride	Sat'd	S	S		
Mercuric Cyanide	Sat'd	S	S	S	S
Mercurous Nitrate	Sat'd	S	S		
Mercury		S	S	S	S
Methyl Alcohol	100%	S	S	S	S
Methyl Bromide		O	U	O	
Methyl Chloride		O	U		
Methyl Ethyl Ketone	100%	U	U	U	U
Methylene Chloride	100%	U	U	U	U
Methylsulfuric Acid		S	S	S	S
Milk		S	S		
Mineral Oils		O	U	S	U
Molasses	Comm.	S	S		
Naphtha	100%	S	U		
Naphtha	100%	S	U		
Naphthalene		U	U		
Nickel Chloride	Sat'd	S	S	S	S
Nickel Nitrate	Con.	S	S	S	S
Nickel Nitrate	Conc.	S	S		
Nickel Sulfate	Sat'd	S	S	S	S
Nicotinic Acid	100%	S	S		
Nitric Acid	0-30%	S	S	S	S
Nitric Acid	30-50%	S	O	S	O
Nitric Acid	70%	S	O	S	O
Nitric Acid	95-98%	U	U	U	U
Nitrobenzene	100%	U	U	U	U
Octyl Cresol		O	U		
Oils and Fats		O	U		
Oleic Acid	Conc.	O	U		
Oleum	Conc.	U	U	U	U
Orange Extract	Dilute	S	S		
Oxalic Acid	Dilute	S	S	S	S

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Oxalic Acid	Sat'd	S	S	S	S
Oxygen	100%	S			
Ozone	100%	O	U		
Perchloric Acid	10%	S	S		
Petroleum Ether		U	U	U	U
Phenol	90%	U	U		
Phosphoric Acid	0-30%	S	S	S	S
Phosphoric Acid	Over 30%	S	S	S	S
Phosphoric Acid	90%	S	U	S	S
Phosphorus (Yellow)	100%	S			
Phosphorus Pentoxide	100%	S	S		
Phosphorus Trichloride		S			
Photographic Solutions		S	S	S	S
Pickling Baths Hydrochloric Acid Sulfuric Acid Sulfuric-Nitric		S S S	S S		
Pickling Baths, Sulfuric Acid Hydrochloric Acid Sulfuric-Nitric		S S S	S S	S S S	S S U
Picric Acid	1%	S	O		
Plating Solutions Brass Cadmium Chromium Copper Gold Indium Lead Nickel Rhodium Silver Tin Zinc		S U S S S S S S S S S S S	S U S S S S S S S S S S S		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Plating Solutions					
Brass		S	S		
Cadmium		U	U		
Chromium		S	S		
Copper		S	S		
Gold		S	S		
Indium		S	S		
Lead		S	S		
Nickel		S	S		
Rhodium		S	S		
Silver		S	S		
Tin		S	S		
Zinc		S	S		
Plating Solutions					
Brass		S	S	S	S
Cadmium		S	S	S	S
Chromium		U	U		
Copper		S	S	S	S
Gold		S	S	S	S
Indium		S	S	S	S
Lead		S	S	S	S
Nickel		S	S	S	S
Rhodium		S	S	S	S
Silver		S	S	S	S
Tin		S	S	S	S
Zinc		S	S	S	S
Potassium Bicarbonate	Sat'd	S	S	S	S
Potassium Borate	1%	S	S	S	S
Potassium Bromate	10%	S	S	S	S
Potassium Bromide	Sat'd	S	S	S	S
Potassium Carbonate		S	S	S	S
Potassium Chlorate	Sat'd	S	S	S	S
Potassium Chloride	Sat'd	S	S	S	S
Potassium Chromate	40%	S	S	S	S
Potassium Cyanide	Sat'd	S	S	S	S
Potassium Dichromate	40%	S	S	S	S
Potassium Ferricyanide	Sat'd	S	S		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Potassium Ferri/Ferro Cyanide		S	S	S	S
Potassium Fluoride		S	S	S	S
Potassium Hydroxide	20% Conc.	S	S	S	S
Potassium Nitrate	Sat'd	S	S	S	S
Potassium Petborate	Sat'd	S	S	S	S
Potassium Perchlorate	Sat'd	S	S		
Potassium Perchlorate	10%	S	S	S	S
Potassium Permanganate	20%	O	U		
Potassium Persulfate	Sat'd	S	S		
Potassium Sulfate	Conc.	S	S	S	S
Potassium Sulfide	Conc.	S	S	S	S
Potassium Sulfite	Conc.	S	S	S	S
Potassium Persulfate	Sat'd	S	S	S	S
Propargyl Alcohol		S	S	S	S
Propyl Alcohol		S	S	S	S
Propylene Dichloride	100%	U	U		
Propylene Glycol		S	S	S	S
Rayon Coagulating Bath		S	S	S	S
Sea Water		S	S	S	S
Selenic Acid		S	S		
Shortening		S	S	S	S
Silicic Acid		S	S	S	S
Silver Nitrate Sol'n		S	S	S	S
Soap Solution	Conc.	S	S	S	S
Sodium Acetate	Sat'd	S	S	S	S
Sodium Benzoate	35%	S	S	S	S
Sodium Bicarbonate	Sat'd	S	S	S	S
Sodium Bisulfate	Sat'd	S	S	S	S
Sodium Bisulfite Sat'd	Sat'd	S	S	S	S
Sodium Borate		S	S	S	S
Sodium Bromide Oil Sol'n		S	S	S	S
Sodium Carbonate	Conc.	S	S	S	S
Sodium Chlorate	Sat'd	S	S	S	S
Sodium Chloride	Sat'd	S	S	S	S
Sodium Cyanide		S	S		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Sodium Cyanide		S	S	S	S
Sodium Dichromate	Sat'd	S	S	S	S
Sodium Ferricyanide	Sat'd	S	S	S	S
Sodium Fluoride	Sat'd	S	S	S	S
Sodium Hydroxide	Conc.	S	S	S	S
Sodium Hypochlorite		S	S	S	S
Sodium Nitrate		S	S	S	S
Sodium Sulfate		S	S	S	S
Sodium Sulfide	25%	S	S		
Sodium Sulfide	Sat'd Sol'n	S	S		
Sodium Sulfide	25% to Sat'd	S	S	S	S
Sodium Sulfite	Sat'd	S	S	S	S
Stannic Chloride	Sat'd	S	S	S	S
Stannous Chloride	Sat'd	S	S	S	S
Starch Solution	Sat'd	S	S	S	
Stearic Acid	100%	S	S	S	
Sulfur	Colloidal	S			
Sulfur Dioxide	Dry, 100%	S	S		
Sulfur Dioxide	Wet, 100%	S			
Sulfur Trioxide		S	S		
Sulfuric Acid	0-50%	S	S	S	S
Sulfuric Acid	70%	S	O	S	O
Sulfuric Acid	80%	S	U	S	U
Sulfuric Acid	96%	O	U	O	U
Sulfuric Acid	98% Conc.	O	U	O	U
Sulfuric Acid Fuming		U	U	U	U
Sulfurous Acid		S	S	S	S
Tallow		S	O		
Tannic Acid	10%	S	S	S	S
Tanning Extracts	Comm.	S	S		
Tartaric Acid	10%	S	S		
Tartaric Acid	Sat'd	U	U		
Tetralin		U	U		
Tetrahydrofuran	100%	U	U		
Toluene		U	U	U	U
Tetrachloroethylene	100%	U	U		

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

tech.topic

Chemical Resistance of Polyethylene

Chemical or Solvent	Concentration	LDPE & MDPE		HDPE Resins	
		70°F	140°F	70°F	140°F
Tetrahydrofurane		O	O	O	O
Transformer Oil		O	U	S	O
Trichloroacetic Acid	10%				
Trichloroethylene		U	U	U	U
Triethanolamine	100%	S	U		
Trisodium Phosphate	Sat'd	S	S		S
Turpentine		S	U		
Urea	Upt to 30%	S	S		
Urea		S	S	S	
Urine		S	S	S	S
Vinegar	Comm.	S	S	S	S
Vanilla Extract		S	S		
Wetting Agents		S	S	S	S
Whiskey		S	S	S	
Wines		S	S	S	S
Xylene		U	U	U	U
Yeast		S	S	S	S
Zinc Chloride	Sat'd	S	S	S	S
Zinc Sulfate	Sat'd	S	S	S	S

S = satisfactory (no attack) O = slight attack U = unsatisfactory 70°F = 21°C, 140°F = 60°C

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at [REDACTED].



Lyondell Chemical Company
 1221 McKinney, Suite 700
 P.O. Box 2583
 Houston, Texas 77252-2583
<http://www.Lyondell.com>