

THE AROCLOR® POLYCHLORINATED POLYPHENYLS

Dielectrics for Capacitors & Transformers

TECHNICAL BULLETIN O-FF/1R

"Nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent. MONSANTO MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY OF ANY PRODUCT REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations, and disclaims all liability for any resulting loss or damage."

MONSANTO INDUSTRIAL CHEMICALS CO.,
an operating unit of Monsanto Company
800 No. Lindbergh Blvd., St. Louis, Mo. 63186

GBRN 000135

Table of Contents

GENERAL PHYSICAL PROPERTIES CHART . . .	4
ELECTRICAL APPLICATION OF AROCLOR . . .	7
Dielectrics for Askarel Type	
Capacitors and Transformers	7
Expansion Medium	10

Appendix

Solubility Table	11
Vapor Pressure	12
Vaporization Rates	13
Corrosion Resistance of Structural Materials . . .	14
Viscosity Table	15
Density Table	16
Dermatology & Toxicity	17
Proper Handling of PCB's	18
Safe Handling	19
Shipping Information	19

*Ask your Man from Monsanto for additional
Aroclor literature:*

- Askarel Inspection and Maintenance Guide
- Aroclor® Plasticizers Technical Bulletin
- Thermal® FR Fluid Heat Systems
- Engineering Heat Transfer Data

Aroclor, Therminol, Starox, Santomerse, Formvar, Lustran,
and Resinox are registered trademarks of Monsanto Company.

GBRN 000136

What are the Aroclor® Polychlorinated Polyphenyls

These compounds are a series of chlorinated biphenyls and chlorinated polyphenyls. They range in form and appearance from mobile oily liquids to fine white crystals and hard transparent resins. Aroclor is non-oxidizing, permanently thermoplastic, of low volatility, and non-corrosive to metals. Aroclor is not hydrolyzed by water, alkalis, or acids. The viscous liquids and resins will not support combustion when heated alone, and they impart fire-resistance to other materials.

Crystalline Aroclor is relatively insoluble, but the liquid and resinous compounds are soluble in most of the common organic solvents, thinners and oils. All Aroclor chlorinated compounds are insoluble in water, glycerine or the glycols. Aroclor 5460 is insoluble in the lower molecular weight alcohols; 4465 is only partly soluble in the lower alcohols.

The following table describes the properties of twelve Aroclor chlorinated compounds, each of which is representative of a series.

GBRN 000137

General Physical Properties of the Aroclor® Chlorinated Compounds

Form.....	Aroclor 1221 Colorless mobile oil	Aroclor 1232 Practically colorless mobile oil	Aroclor 1242 Practically colorless mobile oil	Aroclor 1248 Colorless to light yellow- green, clear, mobile oil	Aroclor 1254 Light yellow viscous oil
Color.....	50 Max. (APHA)	50 Max. (APHA)	50 Max. (APHA)	50 Max. (APHA)	50 Max. (APHA)
Acidity — Maximum (Mgm. KOH per Gm.)....	0.014	0.014	0.010	0.010	0.010
Average Coefficient of Expansion.....cc/cc/°C	0.00071 (15°-40°C)	0.00073 (25°-100°C)	0.00068 (25°-65°C)	0.00070 (25°-65°C)	0.00066 (25°-65°C)
Typical Density Specific Gravity..... Pounds per gallon — 25°C(77°F).....	1.162-1.192 (25°/15.5°C) 9.85	1.270-1.280 (25°/15.5°C) 10.55	1.381-1.392 (25°/15.5°C) 11.50	1.405-1.415 (65°/15.5°C) 12.04	1.495-1.505 (65°/15.5°C) 12.62
Distillation Range — ASTM D-20 (Mod.) Corr. °C.....	275°-320°	290°-325°	325°-366°	340°-375°	365°-390°
Evaporation Loss — % — ASTM D-6 Mod. 163°C..... 5 hrs. 100°C..... 6 hrs.	— 1.0 to 1.5	— 1.0 to 1.5	3.0 to 3.6 0.0 to 0.4	3.0 to 4.0 0.0 to 0.3	1.1 to 1.3 0.0 to 0.2
Flash Point — Cleveland Open Cup..... °C °F	141°-150° 296°-302°	152°-154° 305°-310°	176°-180° 348°-356°	193°-196° 379°-384°	None
Fire Point — Cleveland Open Cup..... °C °F	176° 349°	238° 460°	None*	None	None
Pour Point — ASTM D-97..... °C °F	Crystals at 1°C Crystals at 34°F	-35.5° -32°	-19° 2°	-7° 19.4°	10° 50°
Softening Point — ASTM E-28..... °C °F	— —	— —	— —	— —	— —
Refractive Index — D-line — 20°C.....	1.617-1.618	1.620-1.622	1.627-1.629	1.630-1.631	1.639-1.641
Viscosity — Saybolt Universal 210°F (98.9°C) Sec. (ASTM — D-88)	30-31	31-32	34-35	36-37	44-48
130°F (54.4°C)	35-37	38-41	48-56	73-80	260-340
100°F (37.8°C)	38-41	44-51	82-92	185-240	1800-2500

*None indicates — "No fire hazard in testing conditions"

GBRN 000138

Aroclor 1260 Light yellow soft sticky resin	Aroclor 1262 Light yellow sticky clear resin	Aroclor 1268 White to off-white powder	Aroclor 4465 Light-yellow, clear, brittle resin	Aroclor 5442 Yellow trans- parent sticky resin	Aroclor 5460 Clear, yellow- to-amber, brittle resin	Aroclor 2565 Black, opaque, brittle resin
50 max. (APHA)	50 Max. (APHA)	1.5 Max. NPA (molten)	2 Max. NPA (molten)	2 Max. NPA (molten)	2 Max. NPA (molten)	—
0.014	0.014	0.05	0.05	0.05	0.05	1.4
0.00067 (20°-100°C)	0.00064 (25°-65°C)	0.00067 (20°-100°C)	0.00061 (25°-65°C)	0.00123 (25°-99°C)	0.00179 (25°-124°C)	0.00066 (25°-65°C)
1.555-1.566 (90°/15.5°C) 13.50	1.572-1.583 (90°/15.5°C) 13.72	1.804-1.811 (25°/25°C) 15.09	1.670 (25°/25°C) 13.91	1.470 (25°/25°C) 12.24	1.670 (25°/25°C) 13.91	1.734 (25°-25°C) 14.44
385°-420°	395°-425°	435°-450°	230°-320° at 4 mm. Hg.	215°-300° at 4 mm. Hg.	280°-335° at 5 mm. Hg.	—
0.5 to 0.8 0.0 to 0.1	0.5 to 0.6 0.0 to 0.1	0.1 to 0.2 0.0 to 0.06	0.2 to 0.3 0.0 to 0.02	0.2 0.01	0.03 1.5 to 1.7 (at 250°-5 hrs.)	0.2 to 0.3 —
None	None	None	None	247° 477°	None	None
None	None	None	None	> 350° > 662°	None	None
31°	35°-38°	—	—	46°	—	—
88°	99°	—	—	115°	—	—
—	—	150° to 170° (hold pt.)	60° to 66°	46° to 52°	98° to 105.5°	66° to 72°
—	—	302° to 338° (hold pt.)	140° to 151°	115° to 126°	208° to 222°	149° to 162°
1.647-1.649	1.6501-1.6517	—	1.664-1.667	—	1.660-1.665	—
72-78	86-100	—	90-150 (300°F or 150°C)	300-400	—	—
3200-4500	600-850 (100°F or 71°C)	—	—	—	—	—
—	—	—	—	—	—	—

GBRN 000139

Stability

Toward Alkalies — Aroclor is remarkably resistant to the action of either hydrolyzing agents or high temperature. It is not affected by boiling with sodium hydroxide solution.

Toward Acids — Experiments were made to determine whether hydrogen chloride is evolved during the treatment of Aroclor with sulfuric acid. Aroclor 1254 (selected as typical) was stirred with an equal volume of ten per cent sulfuric acid for a period of 150 hours. Any gases escaping from the reaction flask had to pass through a trap filled with silver nitrate solution, which would give a precipitate of silver chloride if any HCl came in contact with it. After 150 hours of treatment, neither the trap solution nor the acid layer in the treating flask showed any hydrogen chloride present.

Even prolonged treatment (255 hours) with concentrated sulfuric acid indicated negligible effect.

Toward Oxidation — When Aroclor is subjected to a bomb test at 140°C with 250 pounds oxygen per square inch, there is no evidence of oxidation as judged by development of acidity or formation of sludge.

Electrical Resistivity

Aroclor has extremely interesting electrical characteristics: high resistivity and dielectric strength and low power factor. The dielectric constant ranges from 3.4 to 5.0 at 100°C and 1000 cycles, depending upon the particular Aroclor.

Solubility

All Aroclor chlorinated compounds are insoluble in water. They are soluble, however, in most of the common solvents, plasticizers, and resins.

Electrical Applications of Aroclor

Aroclor is one of the purest commercial chemical compounds, virtually free of even traces of conducting impurities. For this reason, dielectric properties of Aroclor closely approximate the theoretical maximum for these particular organic compounds. With its stability, heat-resistance and fire-resistance — Aroclor can be used for a variety of heavy-duty dielectric applications, in hermetically sealed systems.

Dielectrics for Askarel Type Capacitors and Transformers

Aroclor is used per se in capacitors and is formulated for the liquid coolant-insulation fluids in transformers. Such dielectrics must be highly pure with dependably minimal traces of electrolytes. They must be chemically stable and non-corrosive to a wide variety of structural materials. Most important, the dielectric fluid must be fire-resistant.

Aroclor is the only liquid in low cost commercial supply that meets these exacting requirements.

Aroclor liquids 1242, 1248, 1254, and 1260 are used directly, or are carefully formulated with chlorinated benzene and other additives to make askarel fluid for particular needs. Typical formulated askarel fluids are shown on the following pages.

Aroclor liquids 1242 and 1254, themselves or in special formulations, are used as the dielectric in fixed paper capacitors, for the power factor correction in utility transmission lines; for home appliances such as air conditioners, furnaces, washers and driers; for electric motors; and for ballast in fluorescent fixtures. There are also a number of applications in DC systems, in condensers, and the new energy storage capacitors.

ELECTRICAL PROPERTIES

Aroclor	Dielectric Constant at 1,000 Cycles (1)		Volume Resistivity (2) Ohm-cm at 100°C, 500 Volts D.C.	Dielectric Strength (3)	Power Factor (4) 100°C, 1,000 Cycles
	25°C	100°C			
1232	5.7	4.6			
1242	5.8	4.9	Above 500x10 ⁹	Greater than 35KV	<0.1%
1248	5.6	4.6	Above 500x10 ⁹	Greater than 35KV	<0.1%
1254	5.0	4.3	Above 500x10 ⁹	Greater than 35KV	<0.1%
1260	4.3	3.7	Above 500x10 ⁹	Greater than 35KV	<0.1%
1268	2.5	—			
5442	3.0	4.9	Above 500x10 ⁹		
5454	2.7	4.2			
5460	2.5	3.7			
4465	2.7	3.3			

(1) ASTM D-100-67 (2) ASTM D-257-66 (3) ASTM D-340-66 (4) ASTM D-100-67

GBRN 000141

Typical Transformer Askarel

(MIXTURE OF AROCLOR AND CHLOROBENZENES)

Property

Visc. @ 37.8°C. (ASTM D88)
 Spec. Gravity @ 15.5, 15.5°C., (ASTM D287)
 Color, APHA
 Condition
 Acidity, mg. KOH/g.
 Pour Pt., °C., (ASTM D97)
 Inorganic Chlorides, ppm
 Refractive Index @ 25°C.
 Distillation Range (ASTM D20)
 Corrected for stem and barometric pressure
 First drop
 35%
 55%
 65%
 95%
 Corrosion

Water Content, ppm.
 Resistivity, 100°C., 500v., 0.1" gap
 Dielectric Strength, 25°C.
 Dielectric Constant, 100°C., 1000 cycles*
 Tin Tetraphenyl*
 Burn Point, (ASTM D92)*
 Fixed Chlorine*
 Arc Formed Gases*
 (Oxygen Free Liquid @ 25°C.)
 Electrical Stability*

*Determined by special request.

Typical

41-45 Sec. Saybolt Univ.
 1.563-1.571
 150 max.
 Clear
 0.01 max.
 -44°C., or lower
 0.10 max.
 1.6075-1.6085
 210°C., min.
 240-256°C.
 290-330°C.
 385-400°C.
 395-415°C.

After heating with aluminum for 6 hrs. @ 200-220°C., the aluminum must not be corroded either on visual or weight inspection.

The askarel fluid meets the following specifications:

Color, APHA	200 max.
Acidity, mg. KOH/g.	0.01 max.
Inorg. Chlorides, ppm	5 max.
Condition	Clear

30 max.
 100 x 10⁹ ohm-cm., min.
 35 KV., min.
 3.8-4.2
 0.125% ± 0.01% by weight
 None up to Boiling Point
 60.5 ± 0.5

Total combustible gases including carbon monoxide, hydrogen and volatile hydrocarbons.

After heating for 96 hours @ 100°C in a closed container, the resistivity should not decrease more than 10%.


GBRN 000142

Typical Capacitor Aroclor

Property	Typical								
Visc. @ 37.8°C. (ASTM D88)	82-92 seconds Saybolt Univ.								
Specific Gravity @ 25/15.5°C (ASTM D287)	1.381-1.392								
Color, APHA	50 max.								
Condition	Clear								
Acidity, mg. KOH/g.	0.01 max.								
Pour Pt., °C. (ASTM D97)	-14 or lower								
Inorganic Chlorides, ppm	0.10 max.								
Refractive Index @ 25°C.	1.6240-1.6260								
Distillation Range (ASTM D20) Corrected for stem and barometric pressure	10% 325°C. min. 90% 360°C. max.								
Corrosion	After heating with aluminum for six hours at 210°C ± 10°C the aluminum must not be corroded either on visual or weight inspection and the Aroclor 1242 should meet the following specs:								
	<table border="0" style="width: 100%;"> <tr> <td style="width: 70%;">Color, APHA</td> <td>60 max.</td> </tr> <tr> <td>Acidity, mg. KOH/g.</td> <td>0.01 max.</td> </tr> <tr> <td>Inorg. Chlorides, ppm</td> <td>0.10 max.</td> </tr> <tr> <td>Condition</td> <td>Clear</td> </tr> </table>	Color, APHA	60 max.	Acidity, mg. KOH/g.	0.01 max.	Inorg. Chlorides, ppm	0.10 max.	Condition	Clear
Color, APHA	60 max.								
Acidity, mg. KOH/g.	0.01 max.								
Inorg. Chlorides, ppm	0.10 max.								
Condition	Clear								
Water Content, ppm	35 max.								
Resistivity 100°C. 500 volts-DC @ 0.1" gap	500 x 10 ⁹ ohm-cm., min.								
Dielectric Constant 100°C. @ 1000 cycles (ASTM D924)	4.7-4.9								
Flash Point Cleve. Open Cup*	170°C., min.								
Fire Point °C.*	None to boiling point								
Sulfates (ASTM-D117-31)*	None								
Fixed chlorine content (Carius)*	41.5-42.5%								
Specific Heat @ 25°C.*	0.29								
Evaporation @ 100°C for 6 hrs.*	0.4% max.								
Dielectric Strength (KV) (ASTM D877)*	35 Min.								

*Determined by special request.


DIELECTRIC CONSTANT VS. TEMPERATURE
Aroclor® 1242 & Aroclor® 1254



COURTESY OF THE JOURNAL OF FRANKLIN INSTITUTE AND BELL TELEPHONE LABORATORIES

GBRN 000143

**HEAT CAPACITY OF AROCLOR® LIQUIDS
at Various Temperatures**



THERMAL CONDUCTIVITY OF AROCLOR 1248

Temperature		BTU./Hr./Sq. Ft./ °F./°F.	Calories, gram. Sec./ Sq.Cm./°C./Cm.
°C.	°F.		
30	90	0.0680	281×10^{-6}
60	140	0.0687	284×10^{-6}
100	212	0.0697	288×10^{-6}

The average coefficient of expansion of Aroclor 1248 per degree F within the various temperature ranges indicated in the table below was determined by using the simple formula $V_t = V_{t_1} [1 + a (t - t_1)]$. The coefficient a, has been calculated at 100°F increments as follows:

Temp. Range °F	Average Coefficient of Expansion a , /°F
0 to 100	0.00037
100 to 200	0.00039
200 to 300	0.00040
300 to 400	0.00046
400 to 500	0.00048
500 to 600	0.00051

The specific volume of aroclor 1248 at different temperatures is as follows:

Temp. °F	Specific Volume ml./gm
0	0.674
100	0.699
200	0.726
300	0.755
400	0.790
500	0.828
600	0.870

GBRN 000144


**SOLUBILITY OF AROCLOR® CHLORINATED COMPOUNDS IN 100 MILLILITERS
OF VARIOUS SOLVENTS**

Type of Solvent	1242		1248		1254		1270		4468		5460 25°C
	25°C	Hot	25°C	Hot	25°C	Hot	Cold	Hot	Cold	Hot	
Acid											
Acetic Acid	S	S	—	—	S	S	—	—	SS	S	—
Oleic Acid	S	S	—	—	S	S	—	—	S	VS	—
Benzoic Acid	10.0 MP	—	10.0 MP	—	—	—	—	—	—	—	—
Aldehyde											
40% Formaldehyde	I	I	I	I	I	I	I	I	I	I	—
Parfural	VS	VS	VS	VS	VS	VS	SS	SS	VS	VS	—
Amine											
Aniline	S	S	—	—	S	S	—	—	VS	VS	—
Pyridine	132.5 MP	440 MP	—	—	114 MP	425 MP	—	—	VS	VS	—
Chloro — derivatives											
Amyl chlorides—mixed	S	S	S	S	S	S	—	—	VS	VS	—
Carbon Tetrachloride	S	S	S	S	S	S	3.7	—	VS	VS	158
Chloroform	S	S	S	S	S	S	—	—	VS	VS	—
Dichloroethylene	—	—	—	—	—	—	3.0	—	VS	VS	—
Ethylene Dichloride	S	S	S	S	S	S	—	—	VS	VS	—
Monochlorobenzene	S	S	S	S	S	S	2.9	—	VS	VS	—
Orthodichlorobenzene	—	—	—	—	—	—	—	—	VS	VS	—
Tetrachlorethane	S	S	S	S	S	S	—	—	VS	VS	—
Trichlorethane	S	S	S	S	S	S	3.5	—	VS	VS	—
Trichlorethylene	S	S	S	S	S	S	—	—	VS	VS	—
Drying Oil											
Tung Oil	S	S	S	S	S	S	—	—	VS	VS	—
Linseed Oil	S	S	S	S	S	S	—	—	VS	VS	—
Ester											
Amyl Acetate	S	S	S	S	S	S	—	—	VS	VS	—
Butyl Acetate	S	S	S	S	S	S	—	—	VS	VS	—
Cellosolve Acetate	S	S	S	S	S	S	—	—	VS	VS	—
Cottonseed Oil	S	S	S	S	S	S	—	—	S	VS	—
Dibutyl Phthalate	S	S	S	S	S	S	—	—	S	VS	—
Diethyl Phthalate	S	S	S	S	S	S	—	—	S	VS	—
Ethyl Acetate	S	S	S	S	S	S	—	—	S	VS	—
Ethyl Lactate	S	S	S	S	S	S	—	—	VS	VS	—
Ethylene Glycol Diacetate	S	S	S	S	S	S	—	—	VS	VS	—
Methyl Acetate	S	S	S	S	S	S	—	—	S	S	—
Tricresyl Phosphate	S	S	S	S	S	S	—	—	SS	S	—
Ether: Ethyl Ether	S	S	S	S	S	S	S	S	S	—	—
Ether Alcohol											
Carbitol	224 MP	307 MP	VS	VS	173 MP	259 MP	—	—	SS	—	—
Cellosolve	S	S	S	S	S	S	—	—	S	—	—
Diethylene Glycol	—	—	—	—	—	—	—	—	S	—	—
p-p' Dihydroxy Ethyl Ether	16.5 MP	19 MP	SS	SS	8 MP	10 MP	—	—	SS	—	—
Hydrocarbon											
Benzene	VS	VS	VS	VS	VS	VS	3.5	—	VS	VS	143
Gasoline	VS	VS	VS	VS	VS	VS	—	—	VS	VS	—
Kerosene	VS	VS	VS	VS	VS	VS	—	—	VS	VS	—
Mineral Spirits	VS	VS	VS	VS	VS	VS	—	—	VS	VS	—
Paraffin	2.0 MP	S	2.0 MP	S	—	S	—	—	<5.0	S	—
Pine Oil	S	S	VS	VS	S	S	—	—	S	S	—
Toluene	VS	VS	VS	VS	VS	VS	—	—	VS	VS	142
Turpentine	VS	VS	VS	VS	VS	VS	—	—	VS	VS	—
Xylene	VS	VS	VS	VS	VS	VS	—	—	VS	VS	178
Hydroxy—derivatives											
Amyl Alcohol	S	S	—	—	S	S	—	—	S	S	—
n-Butyl Alcohol	S	S	—	—	S	S	—	—	SS	S	—
Ethyl Alcohol (S-A)	23.5 MP	80.0 MP	—	—	10 MP	28 MP	—	—	SS	—	—
Glycerine	I	I	I	I	I	I	I	I	I	I	—
Methyl Alcohol	42.5 MP	88.5 MP	—	—	15 MP	22.2 MP	—	—	SS	—	—
Phenol—90%	194 MP	S	—	—	SS	S	—	—	S	S	—
Ketone											
Acetone	S	S	—	—	S	S	—	—	S	S	260
Miscellaneous											
Carbon Disulfide	S	S	—	—	S	S	—	—	VS	VS	—
Nitrobenzene	S	S	—	—	S	S	—	—	VS	—	—
Water	I	I	I	I	I	I	I	I	I	I	—

I — Insoluble S — Soluble SS — Slightly Soluble VS — Very Soluble
Figures show grams of Aroclor per 100 milliliters of solvent at 25°C unless otherwise indicated.

®Registered by a registered trademark of Union Carbide and Carbon Co.

VAPOR PRESSURE OF AROCLOR® CHLORINATED COMPOUNDS



VAPORIZATION RATES

Sample	Wt. Loss Gms.	Hours Exposure	Surface Area Cm. ²	Vaporization Rate gms./cm. ² hr./100°C
Aroclor® 1221	0.5125	24	12.28	0.00174
Aroclor 1232	0.2572	24	12.28	0.000874
Aroclor 1242	0.0995	24	12.28	0.000338
Aroclor 1248	0.0448	24	12.28	0.000152
42% chlorinated paraffin	0.0745	48	12.28	0.000126
dioctyl phthalate	0.0686	48	12.28	0.000117
Dutrex® 25	0.0256	24	12.28	0.000087
Aroclor 1254	0.0156	24	12.28	0.000053
Dutrex 20	0.0047	24	12.28	0.000016
Aroclor 1262	0.0039	24	12.28	0.000013
Aroclor 1260	0.0026	24	12.28	0.000009
Aroclor 4465	0.0064	72	12.28	0.000007
Aroclor 1270	0.0045	72	12.28	0.000005
Aroclor 5442	0.0039	72	12.28	0.000004
Aroclor 5460	0.0032	72	12.28	0.000004
Tricresyl phosphate	0.0010	24	12.28	0.000003

*Dutrex is a registered trademark of the Shell Oil Co.

APPROXIMATE VAPOR PRESSURES CALCULATED AT 100° F (37.8° C)

Aroclor® 1232	0.005 mm. Hg.
Aroclor 1242	0.001 mm. Hg.
Aroclor 1248	0.00037 mm. Hg.
Aroclor 1254	0.00006 mm. Hg.

GBRN 000147

13


CORROSION RESISTANCE OF STRUCTURAL MATERIALS

Metals	Aircraft Number					
	1248		1254		4485	5480
	25°C	125°C	25°C	125°C	125°C	125°C
Aluminum.....	R	R	R	R	*RR	RR
Copper.....	R	D	R	D	D	D
Magnesium.....	RR	R	R	R	RR	*RR
Nickel.....	RR	R	R	RR	RR	R
Silver.....	R	R	R	R	R	R
Tin.....	R	R	R	R	R	R
Zinc.....	R	R	R	R	R	RR
Mild Steel.....	RR	R	RR	RR	R	RR
Phosphor Bronze.....	R	D	R	R	R	R
Red Brass.....	D	D	R	D	R	De
Stainless Steel (Type 316).....	RR	RR	RR	RR	RR	RR
Yellow Brass.....	R	Re	R	De	Re	Re
Plastics						
Alkyd Resin No. 46594-12.....	*P	P	*P	P	P	P
Alkyd Resin No. 46594-13A.....	*D	P	*D	P	P	P
Cellulose Acetate (Fibestos).....	D	P	D	P	P	P
Durite ⁽¹⁾ Phenol Furfural Resin.....	*D	P	*R	P	D	P
Formvar® Highly Plasticized polyvinyl formal resins.....	De	T	Pe	T	T	T
Formvar® Low Plasticized polyvinyl formal resins.....	PS	T	PS	T	T	T
Glyptal 1276.....	R	P	D	P	P	P
Glyptal 7136.....	*D	T	*R	T	T	T
Maleic Resin No. 46594-13B.....	P	P	*P	P	P	P
Maleic Resin No. 46594-13C.....	P	P	*R	P	P	P
Methyl Methacrylate.....	*D	P	*D	P	P	P
Lustron® B Polystyrene.....	P	T	P	T	T	T
Resinox® Mineral Filled Melamine-Resin.....	*D	*P	*R	R	*P	*D
Resinox Wood Flour Filled Melamine Resin.....	*D	P	*R	D	R	P
Resinox Mineral Filled Phenol Formaldehyde.....	*D	D	*D	D	R	P
Resinox Wood Flour Filled Phenol Formaldehyde.....	*D	P	*D	*R	D	P
Resinox Rag Filled Phenol Formaldehyde.....	*D	D	*D	*D	*D	P
Urea Formaldehyde Resin (Plaston Co.).....	*D	P	*D	*P	P	P

Meaning of Abbreviations:
 * - Based on weight gain calculated as penetration value shown.
 RR - Excellent resistance - less than 1.0 x 10⁻⁴ cm/day corrosion of 200A in/yr.
 R - Good resistance - less penetration between 1.0 x 10⁻⁴ and 10 x 10⁻⁴ cm/yr or between 0.0004 and 0.004 in/yr.
 D - Decent resistance, penetration between 10 x 10⁻⁴ cm/yr and 100 x 10⁻⁴ cm/yr or between 0.004 and 0.004 in/yr.
 P - Poor resistance - penetration greater than 100 x 10⁻⁴ cm/yr or 0.004 in/yr.
 De - Poor resistance due to visible leak action although weight change indicates greater resistance.
 * - Following the letter indicating resistance symbols material may be better than indicated if safety measured stress-weight loss is followed to entire from condition of the part of test strip exposed to air.
 T - Material does not test at room temperature.
 (1) - Durite is a registered trademark of Duran Chemical Co.


GBRN 000148

VISCOSITY RANGES OF SOME OF THE AROCLOR® CHLORINATED COMPOUNDS



GBRN 000149

DENSITIES OF AROCLOR® CHLORINATED COMPOUNDS AT VARIOUS TEMPERATURES



Dermatology and Toxicology

At ordinary temperatures the Aroclor polychlorinated polyphenyls have not presented industrial toxicological problems. The hazard of potential toxic exposure varies with their volatility: the lower-chlorinated ones, being more volatile, present more of a potential problem from the standpoint of both inhalation and skin contact. When Aroclor is used at elevated temperatures, engineering controls must be applied, either by the use of closed systems or by effective local-exhaust ventilation together with general workroom exhaust.

Inhalation tests on animals indicate that the maximum safe concentration of vapor is in the range of 0.5 to 1.0 milligram of the lower-chlorinated Aroclor compounds per cubic meter of air. The threshold limits (maximum allowable concentration for an 8-hour working day) set by the American Conference of Government Hygienists are 1.0 milligram of the lower-chlorinated Aroclor compounds per cubic meter of air and 0.5 milligram of the more-highly-chlorinated compounds, such as Aroclor 1254, per cubic meter of air.

Schwartz patch tests on 200 volunteers showed that neither Aroclor 1254 alone when applied to gauze nor a polyvinyl chloride film containing 11.5-weight-per cent Aroclor 1254 was a primary irritant or a sensitizer. Canvas coated with an oil-modified alkyd resin (17-weight-per cent of the paint-film solids and 7-weight-per cent of the painted fabric was Aroclor 5460) did not produce primary skin irritancy or sensitization according to the same Schwartz technique. Continuous or repeated skin contact with Aroclor must be avoided because of the possible occurrence of a condition called chlorance. Although reports of this condition caused by Aroclor are rare, it can be produced by excessive skin contact.

The Proper Handling of PCB'S by the Electrical Industry to Avoid Environmental Contamination

Polychlorinated biphenyls (PCB's), better known by various trade names including Aroclor (Monsanto), Pyranol (General Electric Co.), and Inerteen (Westinghouse Electric) are the most commonly used askarel class fire-resistant dielectric fluids for hermetically sealed capacitors and transformers. They have served these essential purposes in a satisfactory and irreplaceable manner for over 40 years.

PCB's are noted for their high order of stability, inertness, low volatility and very low water solubility. For these reasons PCB's will persist, if introduced into the environment. This holds true especially for the more highly chlorinated PCB's, as these members of the family have been found quite refractory to soil organisms and are considered to be essentially non-biodegradable.

Recent studies indicate that typical small amounts of PCB's found in the environment can be harmful to certain species of birds and young marine life.

Therefore it is essential to do all that is possible to avoid environmental contamination with PCB's. To establish guide lines, the FDA indicates as maximums 5 parts per million of PCB in fish and 0.2 parts per million in milk.

PCB's must not be introduced into water or marine areas. Spills or leakage must be contained.

Monsanto, and several others, provide facilities for the proper incineration and destruction of scrap PCB fluids. Such materials can be sent freight prepaid to Monsanto's attention, Supervisor Department A-246, Saugat, Illinois for incineration at 3 cents per pound.

Also, PCB fluids should be removed from solid scrap. For example, discarded transformer coils and cores, should be drained free from PCB's followed by flushing or solvent extraction, using such solvents as perchloroethylene, or trichloroethylene employed in vapor degreasing equipment. The scrap fluid mixtures should then be incinerated under the conditions, as provided by Monsanto to destroy the PCB's.

If additional assistance is required about handling PCB's, please contact Monsanto's PCB environmental coordinator, Mr. W. B. Papa-george, Monsanto Company, 800 N. Lindberg, St. Louis, Missouri 68166; phone (314) 694-4051.

GBRN 000152

Safe Handling

Vapors of the Aroclor liquids at room temperature should not be breathed in a confined space. Vapors evolved at elevated temperatures should not be allowed to be dispersed into the general workroom. Instead, engineering control must be applied to reduce vapor concentrations below the allowable concentrations mentioned above.

Continuous or repeated skin contact with Aroclor must be avoided by the use of gloves and protective garments. If any Aroclor is spilled on the skin, the skin should be washed in the usual manner with a soap solution.

A burn caused by contact with a hot Aroclor should be treated like any ordinary burn. Aroclor adhering to the burned area need not be removed immediately, unless treatment of the burn demands it, in which case either soap and water or repeated washings with a vegetable oil are recommended.

GBRN 000153

TOWOLDMON0002650

DISTRICT SALES OFFICES ALL DIVISIONS

AKRON, OHIO 44313

260 Springside Drive
Montross Development Park
Tel. (216) 666-4111

ATLANTA, GEORGIA 30339

320 Interstate North Parkway
Suite 500
Tel. (404) 432-7111

BOSTON, MASSACHUSETTS 02149

Everett Station
Tel. (617) 387-8010

CHICAGO, ILLINOIS

3158 Des Plaines Ave.
Des Plaines, Illinois 60018
Tel. (312) 296-6688

CINCINNATI, OHIO 45206

1501 Madison Road
Tel. (513) 751-6707

DETROIT, MICHIGAN

500 Northland Towers West
Southfield, Mich. 48075
Tel. (313) 357-0910

HONOLULU, HAWAII 96812

205 Pacific International Bldg.
677 Ala Moana Blvd., P. O. Box 3824
Tel. (808) 531-2744

HOUSTON, TEXAS 77027

1301 Post Oak Tower
5061 Westheimer Road
Tel. (713) 621-9550

LOS ANGELES, CALIFORNIA 90022

6670 E. Flotilla St.
Tel. (213) 723-2482

NEW YORK, NEW YORK 10017

277 Park Avenue
Tel. (212) 822-4111

ST. LOUIS, MISSOURI 63166

800 N. Lindbergh Blvd.
Tel. (314) 694-1000

SAN FRANCISCO BAY AREA

2710 Lafayette, Santa Clara, Calif. 95052
Tel. (408) 243-0414

SEATTLE, WASHINGTON 98121

2112 Third Avenue
Tel. (206) 622-4203

WILMINGTON, DELAWARE 19810

Suite 204, Bancroft Bldg.
3411 Silverdale Road
Tel. (302) 478-4800

MONSANTO, 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

*Additional District Offices
are maintained by:*

Agricultural Division

DECATUR, ILLINOIS 62523
207 Decatur Professional Building
363 South Main Street
Tel. (217) 423-8031

DES MOINES, IOWA 50310
312 Merle Hay Tower
Tel. (515) 276-8803

INDIANAPOLIS INDIANA 46206
Suite 218, 4002 Meadows Drive Building
Tel. (317) 547-9148

KANSAS CITY, MISSOURI 64133
701 Blue Ridge Tower
4240 Blue Ridge Boulevard
Tel. (816) 383-8080

LULING, LOUISIANA 70070
P. O. Box 174
Tel. (504) 784-8263

MANKATO, MINNESOTA 56001
111 Madison East
Tel. (507) 387-3406

MEMPHIS, TENNESSEE 38104
303 Union Plaza Building
1838 Union Avenue
Tel. (901) 278-7811

MUSCATINE, IOWA 52761
P. O. Box 473
Tel. (319) 283-1331

Hydrocarbons & Polymers Division

NEW ENGLAND AREA
730 Worcester St.
Indian Orchard, Mass. 01061
Tel. (413) 788-0911

Lean Oil

EL DORADO, ARKANSAS 71730
Lean Oil Building
Tel. (501) 863-3111

JACKSON, MISSISSIPPI 39209
P. O. Box 10637, Westland Station
Tel. (601) 382-3648

N. LITTLE ROCK, ARKANSAS 72119
410 West 8th Street, P. O. Box 6821
Tel. (501) 378-2437

MEMPHIS, TENNESSEE 38113
1023 Riverside Drive, P. O. Box 13248
Tel. (901) 948-4481

Plastic Products & Resins Division

EUGENE, OREGON 97402
685 Stone Road
Tel. (503) 343-7301

KENILWORTH, NEW JERSEY 07033
North Seventh St. & Monroe Ave.
Tel. (201) 278-2900

NEW ENGLAND AREA
180 Groehval Avenue
Indian Orchard, Mass. 01061
Tel. (413) 788-0911

Textiles Division

CHARLOTTE, NORTH CAROLINA 28210
8230 Fairview Road, Suite 400
Tel. (704) 384-0110

GREENVILLE, SOUTH CAROLINA 29608
McAllister Plaza
P. O. Box 8844, Station B
Tel. (803) 342-8700

NEW YORK, NEW YORK 10001
280 Park Ave.
Tel. (212) 586-8100

8/71

GBRN 000154

2-3227-11-71 LITHO IN U.S.A.

TOWOLDMON0002651

GBRN 000155

Monsanto 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

TOWOLDMON0002652