

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE K0906 LOT 33601

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>2510</u>	<u>1</u>	<u>T. 103</u>		
<u>2440</u>	<u>1</u>	<u>T. 126</u>		

STUMP

TOTAL NET WT. 4950 PKG. N-CODE _____PROD. SPVR. JW DATE 1,7,80 WHSE. OPER. _____

24
247

CG 04 CODE K0-906-D PKG.
 → JAN-3 33601
 EST. WGT. 1377 LBS.

OIC
A

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
K0-906-D (C)	EWK 1/24/78
	DCG 1/26/78
TYPED BY	
rj 3/6/78	

MAKING NOTES

REMARKS

TOTAL WEIGHT 5077# (Req.)

NAME: KROLOR® ORANGE R

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

YAT				247		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				1-4-80		STARTED	3 AM				
TIME				2:30 AM		CAKES USED	52				
RELEASED BY				BQ		WATER ON	5:30				
PRESS	2	22	23	24	25	HRS. WASHED	3				
NO. OF CAKES	46	46	46	52	48	OHMS	0500				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 3						HRS. WASHED					
LOAD on 6 cars.						OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8 oz Jar
DELIVER TO CTJ for color

SAMPLED BY 382 RELEASED BY

- DRYING -

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 16
LUMP WGT. 5029
RELEASED BY

- GRINDING -

MILL 938 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 Env + 1 Pt can
DELIVER TO C T L

DATE MIXED
SAMPLED BY
RELEASED BY

33601
41
367