

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG _____

LOT F2J76

JUN 30 1982

EST. WT. 5547* LBS.

NON-BLEEDING

4/227B3

PROCESSES APPROVED BY

YE-698-D (S) F. POST 10/09/81

ALTERNATE

TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DFS

INSTRUCTIONS		= PRESSING =		RECORD					
					1ST	2ND	3RD	4TH	5TH
VAT	1745			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-17-78			STARTED	5:45 PM				
TIME	2:00			CAKES USED	54				
RELEASED BY				WATER ON	9:00 PM				
PRESS	2	92	54	HRS. WASHED					
NO. OF CAKES	54	54	54	M MHOS	420				
PRESS WITH AGITATION				HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER				M MHOS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				M MHOS					
-----				CAKE CONDITION					
-----				NO CARS LOADED	27	4			
-----				EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY *CD*
RELEASED BY

(EXTRUDED) DRY 10 HRS AT 240 DEG F | LUMP: - OK - WET - SALTS - CONTAMINATED
(NOT EXTRUDED) DRY 10 HRS AT 240 F |

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

NO DRUMS 18
LUMP WGT 541.7

DELIVER

SAMPLED BY

RELEASED B

CO-GRIND PER CTL INSTRUCTIONS

GRINDING

MILL MIKROATOMIZE SCREEN

RFM

SCREEN

RFM

MAX. TEMP DEG F

MAX. TEMP.

SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE

DATE MIXED

SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

SAMPLED BY

RELEASED BY

N39415

76
41
17
0

316

12

312

12

316

12

314

12

300

12

328

12

323

12

304

12

335

12

326

12

314

12

312

12

313

12

323

12

307

12

306

12

304

12

288

12

5413