

FORMULA RECORD					
Exp. No.	Date	7/12/35	Rex. No. 299		
Name	Family Paint Light Lead	Card No. 6	See No. 5		
490	LBS 411 B or 1526	Customer	S. W. Co. Trade Sales		
185	" 53 or 1194	To Match	Established product		
185	" 20 L 9-12-35				
?	" 104	Weight Per Gal.	14.00 Visc.		
?	" 19 1133	Baume	Std. of Fineness 2 M		
?	" 12310	Lbs. Gals. per hour	Mill		
	" 1149 Base	New Std. Sample Required	No		
		Date Rec'd	8-27-35		
		Reason for Revision	To show preference for use of 411 B		
31	GALS. (2)	VOID DATE 12-11-41 BY A.B. Zeller			
6	" (213)				
	" ()				
1	" (12 W)				
17	" (38)				
12	" (348)	Normal Output	100	Approved	
9	" (429)	Est. Mfg. Loss	2%	Formulator	
	" ()	Department	B	Supt.	H.B. Eide
X	" ()	Label Analysis Checked - Date			

FORMULA RECORD				TEMPERARY FORMULA	
Exp. No. <u>2-26-36</u>		Date <u>2-26-36</u>		Rev. No. <u>299</u>	
Name <u>FAMILY PAINT LIGHT LEAD</u>		Card No. <u>7</u>		Sec No. <u>5</u>	
490 LBS.	411 B or 1526	Customer <u>S.W. Co.</u>	Trade Sales		
185 "	33 or 1194	To Match <u>Estate</u>			
185 "	20 L	VOID Weight Per Gal. <u>14.00</u> Visc. <u>A.B.H. St.</u> Baume. <u>114</u> of Fineness <u>100</u> Mfg. <u>100</u> No Label Required Lbs. Gals. per hour <u>100</u>			
?	104				
?	19				
?	12310				
"	11684 Base				
31	GALS. (2)	New Std. Sample Required <u>Yes</u>	Date Rec'd		
9	" (1762)	Reason for Revision <u>Temporary formula to utilize purchased oil.</u>			
1	" (12 W)	Retain present formula for use when temporary formula not effective.			
17	" (38)	<i>Use Card # 6</i> WJB			
9	" (348)	Normal Output <u>100</u>	Approved Formulator <u>[Signature]</u>		
9	" (429)	Est. Mfg. Loss <u>2%</u>	Department <u>B</u> Supt. <u>[Signature]</u>		
"	" ()	Label Analysis Checked-Date			
"	" ()	A135			

MANUFACTURING INSTRUCTIONS:				PRODUCTION			
Reduction: Amount <u>Inter Ext.</u> Reducer Used				Date			
Application: Surface <u>Wood or metal</u> Method <u>Brush</u>				Slip No.			
No. Coats <u>Solid two</u> Undercoater Used				Amount			
Drying Time: Touch <u>8-12 hrs</u> Handle Recoat <u>18-24 hrs.</u>							
Rub <u>Sand</u> Wrap Stencil							
Baking Time and Temp.							
Gloss <u>Oil</u> Film <u>Tough</u>							
Special Tests							
FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	<u>2-27-36</u>		<u>11-30-43</u>	ALLIED RESEARCH	<u>2-27-36</u>		<u>6-30-43</u>
NEWARK	"		"	GIBBSBORO			
KENSINGTON	"		"	DAYTON			
OAKLAND	"		"	DETROIT			
DALLAS	"		"	LONDON			
LOS ANGELES	"		"	AUSTRALIA			
MONTREAL	"		"				
COSTA MESA	"		"				

0007-SWP-061057