

Royal Blue Intense White
Interior Trim Enamel
White
RB-32
First

Actual
3/31/42

Pigment							
461-S Lithopone	2400	67.200	3.95	94.80	4.40	105.	
1901 Titanium Oxide	1200	36.960	15.63	187.56	14.80	177.	
31-290 Ultra. Shade Base	12	1.061	26.92	3.23	26.92	3.	
Vehicle							
(5138) Very Long Synth Solv.	2148	263.130	16.32	350.66	17.36	372.	
(2830)s Mixing Varnish	702	94.630	10.43	73.22	11.02	77.	
(348) Mineral Spirits	1045	158.989	1.65	16.20	1.60	15.	
(4090) Drier	96	10.013	14.35	13.78	14.50	13.	
(4092) Drier	18	2.239	32.04	5.77	31.00	5.	

745.11
119.05
771.
123.

7621 631.222
XXXXX
631.222
0.854
626. Gals.

1.190
.021
.071
1.292
.187
1.479
1.
.
.
1.
.
1.

L.C.L
2.52
2.52
4.25
2.80
2.80

OVER 500.
UNDER 500.

OPA 0000757

N 4764