

GOODS:

ENDURANCE HOUSE PAINT - COTTAGE BROWN

LABORATORY NO.

CONSISTENCY

COST CLASS.

DATE 10/27/55

FOR USE ON

STRAINER

GRIND

CUSTOMER

MILL Pebble

WT. OR BE - Q#

CODE NUMBER	ONE GALLON BATCH			LARGE BATCH			IS AGITATOR REQUIRED	
	PINTS	LBS.	OZS.	GALS.	LBS.	OZS.	VISC.F.B.	TEMP.
ZW-37			13				95-105"	
R-210			8-1/2				VISC. RED.	TEMP.
B-7			3/8				VISCOSIMETER #4 Ford Cup	
W-180			5				COLOR.	SHEEN Gloss
W-140			8				NON VOL.	FLASH PT.
W-195			1				MATCH FOR Y-1812 Porcelain	
VM-308			1/2				REDUCER S-43	
CH-185			1/2				A.M.T. FOR BRUSHING FB	
V-872	1						SPRAYING	TUMBLING
O-5	1						DIPPING	DRIP TIME
Grind and add:							BAKE	TEMP.
O-5	7/16						AIR DRIES IN 6-8 hrs.	
V-872	5-3/8						A. D. TO RECOAT IN 48 hrs.	
S-43	3/16						REMARKS:	
D-75			1					
D-68			3/8					
VM-432			1					
CH-269			1/8					
YIELD	1.09						FORMULATOR OK. PCH	28-9

FORMULA NO. Y-1812-J

GOODS: Endurance House Paint-#720 Cottage Brown

LABORATORY NO.

CONSISTENCY: Liquid

COST CLASS: 100-200 Mesh DATE 2/17/54

FOR USE ON

STRAINING: Strained 6

CUSTOMER

10/13/41 85-D-70

MILL: Pebble WT. OR BE 9#

DISCONTINUED

CODE NUMBER	ONE GALLON BATCH			SEE GALS.	LARGE BATCH			IS AGITATOR REQUIRED
	PINTS	LBS.	OZS.		LBS.	OZS.		
YW-37			13				VISC. F.B. 95-105"	TEMP. 80"
R-210			8-1/2				VISC. RED.	TEMP.
B-7			3/8				VISCOSIMETER	1/4 Ford Cup
W-170			1-1/2				COLOR	Brown SHEEN Gloss
W-140			8				NOV VOL.	7/265 FLASH PT.
W-195			1				MATCH FOR	Y-1812 Porcelain Panel
VM-308			1/2				REDUCER	S-43
CH-185			1/8				AMT. FOR BRUSHING	F.B.
							SPRAYING	8:1 S-42 TUMBLING
V-872	1						DIPPING	DRIP TIME
O-5	2-7/16						BAKE	TEMP.
V-872	5-3/8						AIR DRIES IN	6-8 hrs.
S-43	3/16						A. D. TO RECOAT IN	48 hrs.
D-75			1				REMARKS:	
D-68			3/8				Add 1 Oz/gal.	67-T-50
VM-432			1				if necessary.	
CH-243			1/16					
Reformulated to improve gloss & leveling								
YIELD	1.09 Gal.						FORMULATOR	Southwick
								28-8-6

Standard Formula
Not to be taken
from File

GOODS #720 Cottage Brown Endurance Paint

FORMULA NO. Y-1812-B Alt.

CONSISTENCY Liquid

LABORATORY NO. For Cleveland C

FOR USE ON

COST CLASS.

DATE 8/21/51

CUSTOMER

STRAINER

GRIND 3-4

MILL Pebble

WT. OR BE 12.2

CODE NUMBER	ONE GALLON BATCH			LARGE BATCH			IS AGITATOR REQUIRED	
	PINTS	LBS.	OZS.	GALS.	LBS.	OZS.	VISC. F.B.	TEMP.
YW-37		1	4				75-80 KU	TEMP.
R-210			13				VISCOSIMETER	Stormer
W-35			15-7/8				COLOR	SHEEN
W-1			6-1/8				NON VOL.	FLASH PT.
B-7			1/2				MATCH FOR Y-1812 Porcelain Panel	
W-10		1	8				REDUCER	
W-16		1	8				AMT. FOR BRUSHING	
W-150		1	11				SPRAYING	TUMBLING
O-1	2-3/8						DIPPING	DRIP TIME
O-286	2-1/4						BAKE	TEMP.
S-43	2-1/8						AIR DRIES IN	
V-112	5/8						A. D. TO RECOAT IN	
D-10	5/8						REMARKS:	
							FORMULATOR Heidsloff	
YIELD							6-4	

Standard Formula.
Not to be taken
from File

COST	DATE	ANALYSIS		CUSTOMERS
		PIGMENT	52.4 %	Glidden Endurance House Paint
		VEHICLE	47.6 %	#720 Cottage Brown
			100.0 %	
				8/21/51
		PIGMENT		
		Iron Oxide	21.9 %	For Cleveland Only
		Basic Lead Sulphate	4.7	
		10% Leaded Zinc Oxide	12.1	<i>Cleveland Only - 10-12-51</i>
		Carbon	0.4	
		Barium Sulphate	18.4	
		Silica	18.4	
		Magnesium Silicate	24.1	
			100.0 %	
		VEHICLE		
		Linseed Oil	61.7 %	
		* Varnish	7.7	
		Mineral Spirits	23.4	
		Driers	7.2	
			100.0 %	
		* Non-Volatile (Treated		
		Rosin, Tung Oil)	57.0 %	
		Mineral Spirits	43.0	
			100.0 %	
		V-1812	158	

GLD059058

FORMULA RECORD						Formula No. Y-1812-H		
720 Cottage Brown End. Paint						Laboratory No.		
Cr. 12.5 Liquid						Cost Class.		
For use on						Date 12/1/49		
Customer						Strainer		
						Grind 3-4		
						Mill Pebble		
						Wt. or B. 12.2		
Code		One Gallon Batch			Large Batch		Is agitator required	
Number	Pints	Lbs.	Ozs.	Gals.	Lbs.	Wt. 12.2	Temp.	
YW-37		1	4		100	Viscosity 75-80	Temp KU	
R-18		1			80	Viscosimeter Stornor		
W-35			15-7/8		79	Color	Sheen	
W-1			6-1/8		31	Non Vol.	Flash Pt.	
B-7			3/4		3-3/4	Match for Y-1812	porcelain	
W-10		1	8		120	Panel		
W-16		1	8		120	Reducer		
V-181		1	8		120	Amt. for brushing		
						Spraying	Tumbling	
O-1	2-3/8			23-3/4		Dipping	Drip time	
O-286	2-1/4			22-1/2		Bake	Temp.	
D-10	5/8			6-1/4				
S-43	2-1/8			21-1/4		Air dries in		
V-112	5/8			6-1/4		A. D. to recoat in		
Remarks:								
Changed to replace W-6 with W-35 and W-1								
Standard Formula								
to be taken								
from file.								
Formulator H. G. H.								
Yield								

GLD059059

Cost	Date	Analysis	Customers
		Pigment 52.4 %	
		Vehicle 47.6 %	
		Pigment	
		Oxide of Iron	21.9%
		Basic Sulfate of Lead	4.7
		10% Leaded Zinc Oxide	12.1
		Carbon	0.4
		Barium Sulfate	18.4
		Silica	18.4
		Silicates	24.1
			100.0%
		Vehicle	
		Linseed Oil	61.7 %
		Drier	7.2
		* Varnish	7.7
		Mineral Spirits	23.4
			100.0 %
		Non Volatile 56% (Tung Oil, Lined Rosin)	56%
		Volatile (Mineral Spirits)	44%
			100%

GLD059060

FORMULA RECORD

Goods *920 Cellulose Acetate Solution*

Formula No. *Y 1812 G*

Consistency *Liquid*

Date *11-19-45*

Laboratory No.

For Use on *P*

Cost Classification

Code Number	One Gallon Batch			Gallon Batch			Gallon Batch			Manufacturing Specifications
	Pints	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
<i>Y 1812 G</i>		<i>1</i>	<i>4</i>					<i>100</i>		Grind <i>Coar. B</i>
<i>R-18</i>		<i>1</i>						<i>80</i>		Kind of Mill
<i>W-6</i>		<i>1</i>	<i>6</i>					<i>110</i>		Strainer
<i>B-9</i>			<i>3 1/4</i>					<i>3</i>	<i>12 1</i>	Weight per Gallon <i>12.2</i>
<i>W-10</i>		<i>1</i>	<i>8</i>					<i>120</i>		Light Baume Temp.
<i>W-16</i>		<i>1</i>	<i>8</i>					<i>120</i>		Heavy Baume Temp.
<i>W-181</i>		<i>1</i>	<i>8</i>					<i>120</i>		Viscosity <i>25-85</i> Temp. <i>H</i>
										Viscosimeter <i>Standard</i>
<i>Q-1</i>	<i>2 3/8</i>						<i>2 3/8</i>			Flash Point
<i>Q-281</i>	<i>2 1/4</i>						<i>2 1/4</i>			Is Agitator Required
<i>Q-10</i>	<i>5/8</i>						<i>6 1/4</i>			Remarks <i>discontinued</i>
<i>S-43</i>	<i>2 1/4</i>						<i>2 1/4</i>			
<i>T-11</i>	<i>5/8</i>						<i>6 1/4</i>			
										Standard Formula
										Not to be taken
										from file
DISCONTINUED										
SEE <i>12/1/49</i>										
<i>3/18/12#</i>										
										Match <i>y. Bk. Preslon</i>
										<i>Gall.</i>
										<i>3.71 gal/gal</i>

Characteristics and Method of Using		Cost Data		Customers
Type of Goods	House Paint			
Color	Porters Brown			
Luster	Gloss			
Match for	Y. 18121			
Kind of Reducer				All plants 11-21-4
Amount of Reduction for	Pigment	52	4%	
Brushing	F.B.	47	6%	
Spraying	Pressure	100	0%	
Dipping	Drip Time	ANALYSIS		
Floccing	Drip Time	Iron Oxide	21	7%
Tumbling		Barium Sulfate White Lead	5	9%
Air dry to recoat	24 hours	Iron Oxide	10	9%
To Sand or Rub		Carbon	7	7%
Bake Time	Temp.	Barium Sulfate	18	4%
Rub with		Silica	18	4%
Polish with		Silicates	24	1%
Schedule			100	0%
		Waxes		
		Linseed Oil	61	7%
		Stearin	7	2%
		Woolish	7	7%
		Mineral Spirits	23	4%
			100	0%

FORMULA RECORD

Goods Cottage Brown Endurance Paint Formula No. Y-1812 F

Consistency Low

Date 5-12-40

Laboratory No. 100-100000

Free Use On

Cost Classification

[illegible]

DISCONTINUED

GLD059065

[illegible]

GLD059066

DISCONTINUED

Consistency Liquid Data 5-12-41 Laboratory No.

For Use on	Cost Classification
------------	---------------------

GLD059067

Characteristic and Method of Using		Cost Data		Customers
Type of Goods				
Color				
Laster				
Match for				
Kind of Reducer				
Amount of Reduction for				
Brushing				
Spraying	Pressure			
Dipping	Drip Time	Analysis		
Floccing	Drip Time	Pigment	52.5	
Tumbling		Vehicle	47.5	
Air dry to recoat			100.0	
To Sand or Rub		Pigment		
Bake Time	Temp.	Iron Oxide		12.6
Rob with		Zinc Oxide		9.8
Polish with		Basic Lead Sulphate		5.2
Schedule		Carbon		.4
		Barium Sulphate		42.0
		Magnesium Silicate		23.8
		Vehicle		100.0
		Linseed Oil		92.0
		Liquid Drier		8.0
				100.0

GLD059068

FORMULA RECORD	
Goods <i>Cottage Brown End Paint</i>	Formula No. <i>4182F</i>
Consistency <i>Solid</i>	Date <i>4-26-39</i>
For Use on	Cost Classification

Formula No. 2152F

Date 4-26-59

Laboratory No.

Cost Classification

[illegible]

Characteristics and Method of Using		Cost Data		Customers
Type of Goods				
Color				
Exterior				
Match for				
Kind of Reducer				
Amount of Reduction for				
Brushing				
Erspraying	Premure			
Dipping	Drip Time	Kernach Analysis	52.5	
Floccing	Drip Time	Whicla	47.5	
Tumbling				
Air dry to recast		Kernach - Ferric Oxide	18.8	
To Sand or Rub		Thin Oxide	9.8	
Bake Time	Tamp	Powdered Sulfate	5.2	
Rub with		Carbon	0.4	
Polish with		Potassium Sulfate	42.0	
Schedule		Silica & Silicates	23.8	
			10.0 - 5.70	
		Whicla - Linseed Oil	92.0	
		Liquid Sliver	4.5	
		Miscellaneous	3.5	
			100.0 - 5.70	

GLD059070

ALBION 100 A 100 LAC
GELTOS

COTTAGE BROWN ENDORANCE

FORMULA-RECORD

TORONTO

FORMULA NO.

CONSISTENCY

LABORATORY NO.

Y 1812

FOR USE ON

COST CLASS

DATE 4.9.64

CUSTOMER

STRAINER

GRIND 6

MILL

BALL

WT. OR BE 11

CODE NUMBER	100 GALLON BATCH			GALLON BATCH			IS AGITATOR REQUIRED	
	GALS.	LBS.	OZS.	GALS.	LBS.	OZS.	WISC. F.B.	TEMP.
YW 89		110.					90-95"	ROOT
R 18		60.					WISC. RED.	TEMP.
W 180		30.					VISCOSIMETER	#4 RED FORTY CUP
B 7		1.5					COLOR	SHEEN
M 333		5.					NON VOL.	FLASH PT.
CH 185		5.					MATCH FOR	
W 218		5.		PREMIX AND INCLUDE			REDUCER	
S 72	0.25						AMT. FOR BRUSHING	F.B.
V 869	76.						SPRAYING	TUMBLING
O 265	12.						DIPPING	GRIP TIME
S 43	7.58						BAKE	TEMP.
TV 127	1.							
VM 430	0.06						AIR DRIES IN	6-8 HRS.
VM 433	0.11						A. D. TO RECOAT IN	O.N.
VM 432	1.5						REMARKS: FOR BETTER COLOR MATCH	
14 200	0.125						FORMERLY 85D20	
							Y1812J(CAN.)	
							3.26.58	
							CANADIAN MEASURE	
							FORMULATOR (AIR, I.W./O.W.H.)	
YIELD								

GLD059071

COST DEPARTMENT RECORD

DISCONTINUED

FORM 1-1-11 (REVISED 11-1-11)

Goods: Cottage Brown Enl. Paint

Classified Formula No. 1-1-11

Laboratory Formula No.

Consistency

Date 5-25-12

Factory Letter No.

For Use on

Production No. 937-165

Customer A. A. B.

Cost Classification

Ingredient Code Number	Lab'y Formula	Large Batch		Do not write in these columns For Cost Department Use Only						Manufacturing Specifications
		Pounds	Gallons							
1-37	53-1/8 #									Grind. C
1-5	58-7/16 #									Kind of Mill Stone
1-125	30 #									Strainer Coarse
1-7	1-21/64 #									Weight per Gallon 13.14 Spd.
1-10	161-1/4 #									Light Baume Temp.
1-11	53-1/8 #									Heavy Baume Temp.
16-9-902	76-8-902	76-8-915								Viscosity Temp.
1-1	74-17/32 #									Viscosimeter
1-61	2-21/32 #									Flash Point
1-121 Blend	2-21/32 #									Is Agitator Required
1-10 Spec.	2-21/32 #									Formulator

GLD059073

Characteristics and Method of Using		Cost Data				Remarks
Type of Goods		Date	Bulk Cost	Date	Bulk Cost	
Color						
Luster						
Match for						
Kind of Reducer						
Amount of Reducer	Brushing					
	Spraying					
	Dipping					
	Flacbing					
	Tumbling					
Air dry to recoat						
To Sand or Rub						
Bake Time	Temp.					
Rub with						
Polish with						
Schedule						
COOL-CELVINEA 1220000 1220000						

GLD059074

FORMULA RECORD

Formula No. 3 1812 H

Date: 12/1/92 Lab No:

Cost Classification

Discontinued			
red	4/1/12		

Pigment 53%
 Vehicle 47%
 100%

Pigment -

Iron Oxide (Fe-2O3) 21%
 35% Leaded Zinc Oxide 16%
 Barium Sulphate 41%
 Silica & Silicates 21.5%
 Lamp Blacks 5%
 100.0%

Vehicle -

Linseed oil 92%
 Liquid Drier 5%
 Mineral Spirits 3%
 100%

Steel Panels 5's

Round Cans 1's - 1/2's - 1/4's

Endurance Paint Prepared Special Label

FORMULA RECORD

Goods

Endurance Paint Cottage Brown

Formula No.

4 1812 D

Consistency

Date

1/18/52

Old No.

For Use on

Cost Classification

Code Number	1	5	1/2 Bbl.	Bbl.	2 Bbl.	Manufacturing Specifications
05	10 gal		10 gal			Grind <i>Good C</i>
04	18 "					Kind of Mill <i>Stone</i>
01	40 "		58 "			Rate per hr.
043	5 "		5 "			Strainer
D10	3 1/2 "		3 1/2 "			Weight per Gallon <i>13 1/4 #</i>
X V 715	2 "		2 "			Light Baume Temp.
67 T 9	2 "		2 "			Heavy Baume Temp.
						Viscosity Temp.
YW 37	100 #					Make of Viscosimeter
OW 6	100 #					Flash Point
Q 18	85 #					Is Agitator Package Required
D 7	2 1/2 #					Remarks
W 10	280 #					<i>1st Grade Paint</i>
W 11	100 #					
* Note - Add V 715 only if needed for body						
Field						

GLD059077

Analysis

Pigment	52.5%
Vehicle	47.5
	<u>100.0%</u>

Pigment	
Ferric Oxide	18.8%
Zinc Oxide	9.8
Basic Lead Sulphate	5.2
Carbon	0.4
Barium Sulphate	42.0
Silicate & Silicates	23.8
	<u>100.0%</u>

Vehicle:-	
Linseed Oil	92.0%
Liquid Drier	4.5
Mineral Spirits	2.0
Moisture	1.5
	<u>100.0%</u>

Steel Pails 5's

Round Cans 1's - 1/2's - 1/4's

Endurance Paint - Prepared "Special Label"

FORMULA RECORD

Goods

COTTAGE BROWN END PAINT

Formula No.

18120

Consistency

Date

2-6-12

Old No.

For Use on

Classification No.

Material	Code	1	5	Bbl.		Manufacturing Specifications
Raw Oil	01			85 gal		Grind
B. Gypsum	05			5 "		Kind of Mill
Fin. H. Oil	063			10 "		Rate per hr.
						Wt. per gal. Baume
Oil	W10			480 "		Strainer Viscosity
Lead. Zinc	W6			120 "		Flash Point
White Van. Oil	R16			200 "		Testing Requirements
Sliver	W16			75 "		Reduce with
Pulp	W11			75 "		Amount
Long Oil	B7			2 1/2 "		Apply by
						Surface
						Drying time
						Baking time
						Match for
						Std. Yield

GLD059079

P... .. 50.0 %
 W... .. 40.0 %
 100.0 %

P... ..

French Yellow Oxide ... 21.0 %
 Brown Lead Sulphate ... 7.5 %
 Zinc Oxide ... 3.8 %
 Silica & Silicate ... 77.7 %
 100.0 %

White Lead

Basic Lead Oxide ... 87.5 %
 Basic Lead Oxide ... 9.0 %
 Lead Oxide ... 4.5 %
 100.0 %

... .. (Paint Preparation) Special Label

... .. 100.0 %

Printed in U.S.A.

Formular No. Y-1812-E

Cottage Brown

Date 11-10-26. Old No.

For Use on

Cost Classification

GLD059083

Pigment 53.8%

Liquid 46.2

100.0%

Pigment:

French Ochre 44.1%

Bitumens 10.9

Red Oxide 17.5

Silica & Silicates 27.3

Carbon .2

100.0%

Liquid:

Linseed Oil 92%

Liquid Drier 8

100%

Weight per gal. 12.3 lbs.

Steel Pails 5s.

Round Cans 1s, 1/2s, 1/4s.

Endurance Paint - Prepared Special Label

Copy to Bureau 3-10

GLD059084