LABORATORY DATA SHEET

REQUEST # 216
PROJECT # 844965
For J. VONDRAKE

CORTEX 130

SUBJECT C O R K re: DETROIT DIESEL ALLISON DATE OCTOBER 6, 1971

	Test Results	Eng. Spec # 223
% Compressibility at 100, psi.	25.0	20 - 40%
% Recovery	80.5	75% min.
GAUGE	.130"	
Tensile, psi.	114	100 min.
Density (lbs./ft^3)	19.8	17 min.
FLOTATION TEST		
3 hrs. in Boiling H_2O	O K	N
XXXXXXXXXXXXXXXXXXXXXXXXXXXX	OKK	
2 hrs. in ASTM Oil #1 at 212°F	O K	N
Flexibility	O K	5
TESTED BY:	C. Pacyniak	

VPD-128-0000682

MADE IN USA VG 2233