PRODUCT NAME = MOLYBDATE ORANGE NON-BLEEDING

CG 01 CODE YE-698-D PKG ____

LOT MAY -0·81-E 1429 AR/AP

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

= PRESSING =

INSTRUCTIONS				
VAT	242			
DATE	5-16			
TIME	710P			
RELEASED BY	JDC			
PRESS	2	92	93	
NO.OF CAKES	54	54	54	

PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

7DS

RECORD	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	8P				
CAKES USED	52				
WATER ON	5 gal				
HRS. WASHED	1½				
OHMS	2600				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	6				

EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 18
LUMP WGT ~~5555~~ 5537

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1429
124
41

3.46 +
0.14 -
3.54 +
0.14 -
3.57 +
0.14 -
3.67 +
0.14 -
3.59 +
0.14 -
3.39 +
0.14 -
3.64 +
0.14 -
2.00 +
0.14 -
25.74 *

1429
124
41

3.36 +
0.14 -
3.46 +
0.14 -
3.61 +
0.14 -
3.41 +
0.14 -
3.33 +
0.14 -
3.46 +
0.14 -
3.47 +
0.14 -
3.41 +
0.14 -
3.38 +
0.14 -
25.74 +
55.37 *

18-DRUMS

DUP050095803