

MEMORANDUM TO FILE

**Analysis of Insulation Material - Main Steam
Line for Homestead 48" Mill Engine**

In February, 1984, two bulk samples were collected from the Main Steam Line of the Homestead 48" Mill Engine. Fiber identification was performed by the Environmental Health Lab. The sample from the top layer of the insulation was found to contain approximately 30-40% amosite asbestos and 5-10% chrysotile asbestos. The sample from the backing layers was found to contain approximately 40-50% amosite asbestos and 5-10% chrysotile asbestos.