MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 110789 LOT 33998

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2714	1	T-278		
2576	1	T-209		
	STUMP			

TOTAL NET WT. 5290 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
JG	1/28/80	

CG 04 CODE KO-789-D PKG. ____

→ 1/25 ~~JAN 24~~ 33998

EST. WGT. ~~1199~~ 1032 LBS.

Full Press

OK! FP

5532

Total Weight 5199# (Req. _____)

PROCESSING INSTRUCTIONS: BATCH UNIT

24
247

PROCESSES	APPROVED B
KO-789-D (I)	EWK 9-21-7
	DCG 9-21-7
	MTW 10-2-7
TYPED BY	
jlc 10-8-76	

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE Y

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	247				
DATE	1-25-80				
TIME	2:40 Am				
RELEASED BY	PCH				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS with AGITATION

WASH TO 5000 OHMS with 35-75°F water

TEST AFTER 6 HOURS

LOAD on 6 cars

TDS

SAMPLES 1 - 8 oz. jar

DELIVER TO CTL for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5T
STARTED	5 Am				
CAKES USED	48				
WATER ON	1PM				
HRS. WASHED	6 HRS				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY TDS

-DRYING-

DRY 16 HOURS AT 220°F L.V.

LUMP: - OK - WET - SALTS - CONTAMINAT

No Record of any PROCESSING loss

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 18

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 5767

SAMPLED BY RELEASED BY BH

-GRINDING-

MILL 938 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env. + 1 Pint Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050095348

33998
41
252

0.00 *

3.17 +
0.14 -
3.13 +
0.14 -
3.02 +
0.14 -
3.24 +
0.14 -
3.14 +
0.14 -
3.06 +
0.14 -
3.06 +
0.14 -
3.25 +
0.14 -
3.02 +
0.14 -
2.97 +
0.14 -
2.94 +
0.14 -
32.46 *

32.46 +
3.15 +
0.14 -
2.96 +
0.14 -
3.13 +
0.14 -
2.95 +
0.14 -
3.04 +
0.14 -
3.11 +
0.14 -
2.80 +
0.14 -
52.62 *

DUP050095349